

SABIC[®] HDPE B5202

HIGH DENSITY POLYETHYLENE

DESCRIPTION

SABIC[®] HDPE B5202 is a material with a high molecular mass, supplied as pellets.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 190 °C and 21.6 kg	2.0	dg/min	ISO 1133
Density	952	kg/m ³	ASTM D1505
MECHANICAL PROPERTIES			
Tensile test ^{(1) (2)}			
stress at yield	25	MPa	ISO 527-2
stress at break	31	MPa	ISO 527-2
strain at break	1000	%	ISO 527-2
tensile modulus	1000	MPa	ISO 527-2
Flexural test			
Flexural modulus	1150	MPa	ISO 178
Flexural strength	26	MPa	ISO 178
Izod impact notched			
at 23 °C	52	kJ/m ²	ISO 180/A
at -30 °C	36	kJ/m ²	ISO 180/A
Hardness Shore D	61	-	ISO 868
ESCR (Strain Hardening), Gp	21	MPa	ISO 18488
ESCR (10% Igepal CO-630), F50	120	h	ASTM D1693B
THERMAL PROPERTIES			
Heat deflection temperature ^{(3) (4)}			
at 0.45 MPa (HDT/B)	79	°C	ISO 75-2
Vicat Softening Temperature			
at 10 N (VST/A)	127	°C	ISO 306
DSC test			
melting point	132	°C	ISO 11357-3
enthalpy change	200	J/g	ISO 11357-3

(1) Test specimen according to ISO 527-2 type 1BA, thickness 2 mm

(2) Speed of testing: 50 mm/min

(3) Compression moulding of test specimen according to ISO 1872-2

(4) Conditioning of test specimen: temp. 23 °C, relative humidity 50 %, 24 hours

QUALITY

SABIC is fully certified in accordance with the internationally accepted quality standard ISO 9001.

STORAGE AND HANDLING

Polyethylenes resins (in pelletised or powder form) should be stored in such a way that it prevents exposure to direct sunlight and/or heat, as this may lead to quality deterioration. The storage location should also be dry, dust free and the ambient temperature should not exceed 50 °C. Not complying with these precautionary measures can lead to a degradation of the product which can result in colour changes, bad smell and inadequate product performance. It is also advisable to process polyethylene resins (in pelletised or powder form) within 6 months after delivery, this because also excessive aging of polyethylene can lead to a deterioration in quality.

HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

Detailed information is provided in the relevant Material Safety Datasheet and or Standard Food Declaration, available on the Internet (www.SABIC.com). Additional specific information can be requested via your local Sales Office.

ENVIRONMENT AND RECYCLING

The environmental aspects of any packaging material do not only imply waste issues but have to be considered in relation with the use of natural resources, the preservations of foodstuffs, etc. SABIC considers polyethylene to be an environmentally efficient packaging material. Its low specific energy consumption and insignificant emissions to air and water designate polyethylene as the ecological alternative in comparison with the traditional packaging materials. Recycling of packaging materials is supported by SABIC whenever ecological and social benefits are achieved and where a social infrastructure for selective collecting and sorting of packaging is fostered. Whenever 'thermal' recycling of packaging (i.e. incineration with energy recovery) is carried out, polyethylene -with its fairly simple molecular structure and low amount of additives- is considered to be a trouble-free fuel.