

SABIC® HDPE B4660AB

HIGH DENSITY POLYETHYLENE

DESCRIPTION

B4660AB grade are medium molecular weight High Density Polyethylene homopolymer for blow molding Applications. They are primarily Designed for imparting high rigidity, toughness and good processability. These unique properties offer the possibility to reduce weight at very good top load strength. B4660AB: Suitable for Water packaging

TYPICAL APPLICATIONS

B4660 Series resins are primarily intended for blow molding bottles for the food and beverage industry. The grade B4660AB is specifically recommended for water packaging applications. The grades are intended to meet customer specifications in respect of purity, healthiness and organoleptic. They can also be used in other hollow thin-walled parts and profile extrusions. They are not recommended for packaging Environmentally active materials such as soaps, detergents, shampoos, etc.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR) ⁽¹⁾			
@ 190°C & 2.16 kg load ⁽¹⁾	0.7	g/10 min	ASTM D1238
@ 190°C & 5 kg load	2.8	g/10 min	ASTM D1238
@ 190°C & 21.6 kg load	46	g/10 min	ASTM D1238
Density at 23°C	961	kg/m ³	ASTM D1505
MECHANICAL PROPERTIES			
1% Secant Modulus	>1000	MPa	ASTM D638
Tensile Strength at Yield	30	MPa	ASTM D638
Tensile Strength at Break	18	MPa	ASTM D638
Tensile Elongation at Break	500	%	ASTM D638
Flexural Strength ⁽²⁾	28	MPa	ASTM D790
Flexural Modulus	1100	MPa	ISO 178/1A
Izod Impact Strength	150	J/m	ASTM D256
Hardness (Shore D)	66	-	ASTM D2240
THERMAL PROPERTIES			
Vicat Softening Point	127	°C	ASTM D1525
Brittleness Temperature	<-75	°C	ASTM D746

(1) Typical values: not to be construed as specification limits.

(2) Based on compression molded sheet.

PROCESSING CONDITIONS

Typical processing conditions for B4660 are:

Barrel temperature: 170-200°C

Melt temperature: 180-210°C