

## POLYMERS

# SABIC<sup>®</sup> HDPE Injection Molding M80064 Series

## PRODUCT DESCRIPTION

M80064 is High Density Polyethylene grade with narrow molecular weight distribution suitable for injection molding applications. It has been designed to give good rigidity, toughness and low warpage. M80064 is also available with UV stabilizer as M80064S.

## TYPICAL APPLICATIONS

M80064 series grades are recommended for crates, molded cases and trays, industrial pails and other similar products requiring toughness and rigidity.

## TYPICAL DATA

PROPERTIES	Unit	Value <sup>(1)</sup>	Test Method
Melt Flow Rate			
@ 190°C & 2.16 kg load	g/10 min	8	ASTM D 1238
Density @ 23°C	Kg/m <sup>3</sup>	964	ASTM D 1505
<b>MECHANICAL PROPERTIES <sup>(2)</sup></b>			
1% Secant Modulus	MPa	950	ASTM D 638
Tensile Strength @ Yield	MPa	26	ASTM D 638
Tensile Strength @ Break	MPa	18	ASTM D 638
Tensile Elongation @ Break	%	>800	ASTM D 638
Flexural Strength	MPa	25	ASTM D 790
Flexural Modulus	MPa	1000	ASTM D 790
Izod Impact	J/m	75	ASTM D 256
Hardness (Shore D)	-	62	ASTM D 2240
ESCR (100% Igepal), F50*	Hrs	3	ASTM D 1693B
ESCR (10% Igepal), F50*	Hrs	2	ASTM D 1693B
<b>THERMAL PROPERTIES</b>			
Vicat Softening Point	°C	125	ASTM D 1525
Brittleness Temperature	°C	< -75	ASTM D 746

(1) Typical values: not to be construed as specification limits.

(2) Based on Injection molded specimens.

\*Based on compression molded sheet