

SABIC® HDPE M300054

HIGH DENSITY POLYETHYLENE

DESCRIPTION

M300054 is a High Density Polyethylene grade with narrow molecular weight distribution suitable for injection molding applications. It has been designed to give good flow properties, low warpage with good dimensional stability and high gloss.

TYPICAL APPLICATIONS

M300054 is recommended for housewares, small containers, caps, cups & tubs and various thin wall articles.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 190°C and 2.16 kg	30	g/10 min	ASTM D1238
Density at 23°C ⁽¹⁾	954	kg/m ³	ASTM D1505
MECHANICAL PROPERTIES			
1% Secant Modulus ⁽²⁾	750	MPa	ASTM D638
Tensile Strength at Yield	23	MPa	ASTM D638
Tensile Strength at Break	12	MPa	ASTM D638
Tensile Elongation at Break	200	%	ASTM D638
Flexural Strength	22	MPa	ASTM D790
Flexural Modulus	800	MPa	ISO 178/1A
Izod Impact Strength	28	J/m	ASTM D256
Hardness (Shore D)	60	-	ASTM D2240
ESCR (100% Igepal), F50 ⁽³⁾	<1	Hrs	ASTM D1693B
ESCR (10% Igepal), F50	<1	Hrs	ASTM D1693B
THERMAL PROPERTIES			
Vicat Softening Point	121	°C	ASTM D1525
Brittleness Temperature	<-75	°C	ASTM D746

(1) Typical values: not to be construed as specification limits.

(2) Based on Injection molded specimens.

(3) Based on compression molded sheet

PROCESSING CONDITIONS

Typical processing conditions for M300054 are:

Melt temperature: 175-230°C

Mold temperature: 15-60°C

Injection pressure: 600 - 1000 Bar