

## SABIC® HDPE P4200RT

HIGH DENSITY POLYETHYLENE FOR PIPE

## DESCRIPTION

SABIC HDPE P4200RT is a high-density polyethylene (HDPE) with high melt viscosity for extrusion. The product provides excellent stress crack resistance properties (ESCR) combined with very good long-term hydrostatic strength, high heat & extremely high extraction stability. It fulfills the requirements of DIN 16833 / ISO 24033 for PE-RT Type II. The material is classified as MRS 10 (PE100) according to ISO 12162.

## **TYPICAL APPLICATIONS**

Typical customer applications are underfloor heating and multilayer pipes for heating and plumbing. Further typical applications are High Voltage cable ducts, pipes for Oil & Gas exploration, district heating media pipes and casing pipes.

It provides good ESCR (environmental stress cracking resistance). It is weldable, has very good heat aging resistance & good organoleptic properties. This grade is suitable for drinking water applications.

## **TYPICAL PROPERTY VALUES**

| PROPERTIES  | TYPICAL VALUES               | UNITS   | TEST METHODS   |
|---|------------------------------|---|--|
| POLYMER PROPERTIES  |                              |   |  |
| Melt Flow Rate (MFR) <sup>(1)</sup>   |                              |   |  |
| @ 190°C & 5 kg load   | 0.45                         | g/10 min  | ISO 1133   |
| @ 190°C & 21.6 kg load  | 9.5                          | g/10 min  | ISO 1133   |
| Density   |                              |   |  |
| @23°C   | 947                          | kg/m <sup>3</sup>   | ISO 1183   |
| MECHANICAL PROPERTIES   |                              |   |  |
| Hardness Shore D <sup>(2)</sup>   | 59                           | -   | ISO 868  |
| Tensile Strength at Yield <sup>(3)</sup>  | 22                           | MPa   | ISO 527-2  |
| Tensile Elongation at Yield <sup>(3)</sup>  | 8                            | %   | ISO 527-2  |
|   |                              | , •   | 50 521 2   |
| Tensile modulus <sup>(3)</sup>  |                              |   |  |
|   | 850                          | МРа   | ISO 899  |
| Tensile modulus <sup>(3)</sup>  |                              |   |  |
| Tensile modulus <sup>(3)</sup><br>Tensile modulus <sup>(3)</sup>  | 850                          | МРа   | ISO 899  |
| Tensile modulus <sup>(3)</sup><br>Tensile modulus <sup>(3)</sup><br>Charpy Impact Notched @ 23°C <sup>(2)</sup>   | 850<br>24                    | MPa<br>kJ/m²  | ISO 899<br>ISO 179   |
| Tensile modulus <sup>(3)</sup> Tensile modulus <sup>(3)</sup> Charpy Impact Notched @ 23°C <sup>(2)</sup> Charpy Impact Notched @ -30°C <sup>(2)</sup>  | 850<br>24<br>8               | MPa<br>kJ/m²<br>kJ/m²                                       | ISO 899<br>ISO 179<br>ISO 179                              |
| Tensile modulus (3)   Tensile modulus (3)   Charpy Impact Notched @ 23°C (2)   Charpy Impact Notched @ -30°C (2)   MRS Classification (4)   | 850<br>24<br>8<br>10         | MPa<br>kJ/m²<br>kJ/m²<br>MPa                                | ISO 899<br>ISO 179<br>ISO 179<br>EN ISO 13479              |
| Tensile modulus <sup>(3)</sup> Tensile modulus <sup>(3)</sup> Charpy Impact Notched @ 23°C <sup>(2)</sup> Charpy Impact Notched @ -30°C <sup>(2)</sup> MRS Classification <sup>(4)</sup> FNCT, (4.0 MPa, 2% Arkopal N100, 800 C)                      | 850<br>24<br>8<br>10         | MPa<br>kJ/m²<br>kJ/m²<br>MPa                                | ISO 899<br>ISO 179<br>ISO 179<br>EN ISO 13479              |
| Tensile modulus <sup>(3)</sup> Tensile modulus <sup>(3)</sup> Charpy Impact Notched @ 23°C <sup>(2)</sup> Charpy Impact Notched @ -30°C <sup>(2)</sup> MRS Classification <sup>(4)</sup> FNCT, (4.0 MPa, 2% Arkopal N100, 800 C)   THERMAL PROPERTIES | 850<br>24<br>8<br>10<br>>350 | MPa<br>kJ/m <sup>2</sup><br>kJ/m <sup>2</sup><br>MPa<br>Hrs | ISO 899<br>ISO 179<br>ISO 179<br>EN ISO 13479<br>ISO 16770 |

(1) Typical values & not to be construed as specification limits.

(2) Based on compression-molded sheet

(3) Test specimen according to ISO 527-2 type 1 BA, thickness 2mm with 50mm/min test speed.

(4) MRS classification testing ongoing.