

# SABIC® LLDPE 118WJA

LINEAR LOW DENSITY POLYETHYLENE  
REGION AMERICAS

## DESCRIPTION

SABIC® LLDPE 118WJA is a butene linear low density polyethylene resin typically used for general purpose applications. Films produced from this resin are tough with good puncture resistance, high tensile strength and good hottack properties. The resin contains slip and antiblock additive. SABIC® LLDPE 118WJA is TNPP free. and the grade contains slip and antiblock additives.  
This product is not intended for and must not be used in any pharmaceutical/medical applications.

## TYPICAL APPLICATIONS

Shipping sacks, ice bags, frozen food bags, stretch wrap film, produce bags, liners, carrier bags, garbage bags, agricultural films, laminated and coextruded films for meat wrap, frozen food and other food packaging, shrink film (for blending with LDPE), industrial consumer packaging, and high clarity film applications if blended with (10~20%) LDPE.

## TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate (MFR)</b>			
at 190 °C and 2.16 kg	1.0	g/10 min	ASTM D1238
<b>Density</b>	918	kg/m <sup>3</sup>	ASTM D1505
<b>OPTICAL PROPERTIES <sup>(1)</sup></b>			
<b>Haze</b>	18	%	ASTM D1003
<b>Gloss (45°)</b>	50	%	ASTM D2457
<b>FILM PROPERTIES <sup>(1)</sup></b>			
<b>Tensile test film</b>			
Stress at break MD	43	MPa	ASTM D882
Stress at break TD	35	MPa	ASTM D882
Strain at break MD	570	%	ASTM D882
Strain at break TD	850	%	ASTM D882
Stress at yield MD	10	MPa	ASTM D882
Stress at yield TD	11	MPa	ASTM D882
Dart Impact Strength	90	g	ASTM D1709
Secant modulus 1% MD	190	MPa	ASTM D882
Secant modulus 1% TD	220	MPa	ASTM D882
Puncture Force	40	N	SABIC method
Puncture Energy	0.8	J	SABIC method
Elmendorf Tear Strength MD	120	g	ASTM D1922
Elmendorf Tear Strength TD	400	g	ASTM D1922
<b>THERMAL PROPERTIES</b>			
<b>DSC test</b>			
melting point	121	°C	SABIC method

(1) Properties have been measured by producing 30 µm film with 2.5 BUR using 100% 118WJ.