

# SABIC® LLDPE 119ZJ

## LINEAR LOW DENSITY POLYETHYLENE

### DESCRIPTION

SABIC® LLDPE 119ZJ is a butene linear low density polyethylene resin produced using solution technology, typically used for general purpose applications. Films produced from this resin are tough with good puncture resistance, high tensile strength and good hottack properties. The resin contains slip and antiblock additive. SABIC® LLDPE 119ZJ is TNPP free.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

### TYPICAL APPLICATIONS

Shipping sacks, ice bags, frozen food bags, stretch wrap film, produce bags, liners, carrier bags, garbage bags, agricultural films, laminated and coextruded films for meat wrap, frozen food and other food packaging, shrink film (for blending with LDPE), industrial consumer packaging, and high clarity film applications if blended with (10~20%) LDPE.

### TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Density</b>			
Density	0.918	g/cm <sup>3</sup>	ASTM D792
<b>Melt Flow Rate (MFR)</b>			
at 190 °C and 2.16 kg	1.0	g/10 min	ASTM D1238
<b>OPTICAL PROPERTIES <sup>(1)</sup></b>			
<b>Gloss</b>			
Gloss (45°)	65	-	ASTM D2457
<b>Haze <sup>(1)</sup></b>	12	%	ASTM D1003
<b>FILM PROPERTIES <sup>(1)</sup></b>			
<b>Dart Impact Strength</b>			
Dart Drop Impact	95	g	ASTM D1709
<b>Elmendorf Tear Strength</b>			
Tear Strength, MD	110	g	ASTM D1922
Tear Strength, TD	255	g	ASTM D1922
<b>Tensile test film</b>			
2% secant modulus, MD	183	MPa	ASTM D882
2% secant modulus, TD	217	MPa	ASTM D882
Stress @ Yield, MD	12.2	MPa	ASTM D882
Stress @ Yield, TD	12.2	MPa	ASTM D882
Stress @ Break, MD	38	MPa	ASTM D882
Stress @ Break, TD	22.9	MPa	ASTM D882
Strain @ Break, MD	630	%	ASTM D882
Strain @ Break, TD	720	%	ASTM D882

(1) Fabrication Conditions are: Die Gap 70mil (1.8 mm), Melt Temperature 226C, output: 55 kg/hr, Die Diameter: 203mm, Blow-up Ratio:2.5:1 and Frost Line Height: 71 cm

## PROCESSING CONDITIONS

Typical processing conditions for 119ZJ are: Melt temperature: 195 - 215°C, Blow up ratio: 2.0 - 3.0

## STORAGE AND HANDLING

Polyethylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

## ENVIRONMENT AND RECYCLING

The environmental aspects of any packaging material do not only imply waste issues but have to be considered in relation with the use of natural resources, the preservations of foodstuffs, etc. SABIC Europe considers polyethylene to be an environmentally efficient packaging material. Its low specific energy consumption and insignificant emissions to air and water designate polyethylene as the ecological alternative in comparison with the traditional packaging materials. Recycling of packaging materials is supported by SABIC Europe whenever ecological and social benefits are achieved and where a social infrastructure for selective collecting and sorting of packaging is fostered. Whenever 'thermal' recycling of packaging (i.e. incineration with energy recovery) is carried out, polyethylene -with its fairly simple molecular structure and low amount of additives- is considered to be a trouble-free fuel.