

# SABIC® LLDPE 318CNJ

LINEAR LOW DENSITY POLYETHYLENE

## DESCRIPTION

318CNJ is a Linear Low Density Polyethylene TNPP free grade designed for wire and cable applications. It contains optimized level of antioxidants and does not contain any slip and antiblock additives. Sufficient antioxidant and Cu-inhibitor should be added to meet specific ageing requirements. For jacketing applications, addition of Carbon Black or UV stabilizer is required.

## TYPICAL APPLICATIONS

One-step or two-step Silane cross-linkable insulation for Low Voltage power insulation cable, Aerial bundle cable and suitable for telecommunication and Low Voltage power cable jacketing.

## TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate (MFR)</b>			
at 190°C and 2.16 kg	2.8	g/10 min	ASTM D1238
<b>Density</b>	918	kg/m <sup>3</sup>	ASTM D1505
<b>MECHANICAL PROPERTIES</b>			
<b>Hardness (Shore D) <sup>(1)</sup></b>	51	-	ASTM D2240
<b>FILM PROPERTIES</b>			
<b>Tensile Properties</b>			
stress at yield	10	MPa	ASTM D638
stress at break	18	MPa	ASTM D638
strain at yield	17	%	ASTM D638
strain at break	555	%	ASTM D638
1% secant modulus	174	MPa	ASTM D638
<b>THERMAL PROPERTIES</b>			
<b>Peak Melting Temperature</b>	120	°C	SABIC method
<b>ELECTRICAL PROPERTIES</b>			
<b>Volume Resistivity</b>			
at 500V	6.8x10 <sup>17</sup>	Ω.cm	ASTM D257
<b>Dielectric Constant</b>			
at 1 kHz	2.25	-	ASTM D150
<b>Dissipation Factor</b>			
at 1 kHz	7.0x10 <sup>-4</sup>	-	ASTM D150
<b>Dielectric Strength</b>			
at 1000 V/sec	37	kV/mm	ASTM D149

(1) Based on Injection molded specimens.