

SABIC® LLDPE 6118NSF

LINEAR LOW DENSITY POLYETHYLENE

DESCRIPTION

SABIC® LLDPE 6118NSF is a hexene linear low density polyethylene resin. Films made from this resin exhibit good tensile strength, stiffness, dart drop impact strength, tear strength and seal/hottack properties. Application: Typical application for SABIC® LLDPE 6118NSF are heavy duty bags, lamination films, agriculture films, stretch wrap films, frozen food packaging and other applications requiring higher impact strength, high tear resistance and improved sealing properties.

Film properties: Film of 50 µm and BUR = 2 has been produced on Kiefel IBC with 140 kg/h. Die size 200 mm, die gap 2.7 mm.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 190 °C and 2.16 kg	0.9	dg/min	ISO 1133
Density	918	kg/m³	ASTM D1505
OPTICAL PROPERTIES			
Gloss (45°)	57	%	ASTM D2457
Haze	13	%	ASTM D1003
FILM PROPERTIES			
Impact strength	35	kJ/m	ASTM D4272
Tear strength TD	400	kN/m	ISO 6383-2
Tear strength MD	100	kN/m	ISO 6383-2
Puncture resistance	750	J/m	SABIC method
Tensile test film			
Yield stress TD	13	MPa	ISO 527-3
Yield stress MD	11	MPa	ISO 527-3
Stress at break MD	47	MPa	ISO 527-3
Modulus of elasticity MD	190	MPa	ISO 527-3
Stress at break TD	40	MPa	ISO 527-3
Strain at break TD	800	%	ISO 527-3
Modulus of elasticity TD	230	MPa	ISO 527-3
Strain at break MD	630	%	ISO 527-3
THERMAL PROPERTIES			
Vicat Softening Temperature			
at 10 N (VST/A)	106	°C	ISO 306
DSC test			
melting point	124	°C	SABIC method