

SABIC® LLDPE 6821NE

LINEAR LOW DENSITY POLYETHYLENE

DESCRIPTION

SABIC® LLDPE 6821NE is a hexene linear low density polyethylene. Films made from this resin exhibit good tensile strength, stiffness, dart drop impact strength, tear strength and hottack properties.

Application

Typical applications for SABIC® LLDPE 6821NE are heavy duty bags, lamination films, agriculture films, stretch wrap films, frozen food packaging and other applications requiring high impact strength and tear resistance.

Film properties

Film of 50 µm and BUR = 2 has been produced on Kiefel IBC with 140 kg/h. Die size 200 mm, die gap 2.7mm.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 190 °C and 2.16 kg	0.8	dg/min	ISO 1133
Density	921	kg/m ³	ASTM D1505
OPTICAL PROPERTIES			
Gloss (45°)	55	%	ASTM D2457
Haze	15	%	ASTM D1003
FILM PROPERTIES			
Impact strength	30	kJ/m	ASTM D4272
Tear strength TD	330	kN/m	ISO 6383-2
Tear strength MD	80	kN/m	ISO 6383-2
*Puncture resistance	70	J/mm	SABIC method
Tensile test film			
Strain at break MD	600	%	ISO 527-3
Modulus of elasticity TD	250	MPa	ISO 527-3
Yield stress TD	13.5	MPa	ISO 527-3
Modulus of elasticity MD	220	MPa	ISO 527-3
Yield stress MD	12	MPa	ISO 527-3
Stress at break MD	45	MPa	ISO 527-3
Stress at break TD	38	MPa	ISO 527-3
Strain at break TD	750	%	ISO 527-3
THERMAL PROPERTIES			
Vicat Softening Temperature			
at 10 N (VST/A)	111	°C	ISO 306
DSC test			
melting point	125	°C	SABIC method