

# SABIC® LLDPE BX202

## LINEAR LOW DENSITY POLYETHYLENE

### DESCRIPTION

SABIC® LLDPE BX202 is a linear low density polyethylene resin typically used for the production of biaxial orientated polyethylene (BOPE) via tenter frame technology. Typical applications are food and non-food packaging. SABIC® BX202 facilitates mono-material PE structures. This grade is also available as certified bio-renewable and circular polymer.

Film properties: Film of 25 µm, produced on commercial tenter frame with >1000 kg/h output.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

### TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate (MFR)</b>			
at 190 °C and 2.16 kg	2.1	dg/min	ISO 1133
<b>Density</b>	921	kg/m³	ASTM D1505
<b>OPTICAL PROPERTIES</b>			
<b>Gloss (45°)</b>	90	%	ASTM D2457
<b>Haze</b>	5	%	ASTM D1003
<b>FILM PROPERTIES</b>			
<b>Dart Impact F50</b>	350	g	ASTM D1709
<b>Tensile test film</b>			
Stress at break MD	70	MPa	ASTM D882
Modulus of elasticity MD	510	MPa	ASTM D882
Stress at break TD	150	MPa	ASTM D882
Strain at break TD	50	%	ASTM D882
Modulus of elasticity TD	850	MPa	ASTM D882
Strain at break MD	230	%	ASTM D882
<b>THERMAL PROPERTIES</b>			
<b>Vicat Softening Temperature</b>			
at 10 N (VST/A)	100	°C	ISO 306
<b>DSC test</b>			
melting point	124	°C	SABIC method

### ENVIRONMENT AND RECYCLING

The environmental aspects of any packaging material do not only imply waste issues but have to be considered in relation with the use of natural resources, the preservations of foodstuffs, etc. SABIC considers polyethylene to be an environmentally efficient packaging material. Its low specific energy consumption and insignificant emissions to air and water designate polyethylene as the ecological alternative in comparison with the traditional packaging materials. Recycling of packaging materials is supported by SABIC whenever ecological and social benefits are achieved and where a social infrastructure for selective collecting and sorting of packaging is fostered. Whenever 'thermal' recycling of packaging (i.e. incineration with energy recovery) is carried out, polyethylene -with its fairly simple molecular structure and low amount of additives- is considered to be a trouble-free fuel.