



LNP™ STAT-KON™ Compound LX00486C

Americas: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound PDX-L-00486 CCS

Product reorder name: LX00486C

LNP™ STAT-KON™ LX00486C is a compound based on Polyetheretherketone containing proprietary fillers. Added features of this grade includes: Clean Compound System, Electrically Conductive.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	1820	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2	%	ASTM D 638
Tensile Modulus, 5 mm/min	176200	kgf/cm ²	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	2670	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	138600	kgf/cm ²	ASTM D 790
Tensile Stress, break, 5 mm/min	177	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.2	%	ISO 527
Tensile Modulus, 1 mm/min	16280	MPa	ISO 527
Flexural Stress	255	MPa	ISO 178
Flexural Modulus, 2 mm/min	13490	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	66	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	6	cm-kgf/cm	ASTM D 256
Multiaxial Impact	23	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	69	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	40	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	336	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	315	°C	ASTM D 648
CTE, -30°C to 30°C, flow	1.1E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	4.1E-05	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	330	°C	ISO 75/Bf



LNP™ STAT-KON™ Compound LX00486C

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	291	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.4	-	ASTM D 792
Density	1.4	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.05	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.25	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1.3	%	ASTM D 955
Moisture Absorption (23°C / 50% RH)	0.08	%	ISO 62
ELECTRICAL			
Surface Resistivity	1.E+04 - 1.E+07	Ohm	ASTM D 257



LNP™ STAT-KON™ Compound LX00486C

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	150	°C
Drying Time	4 - 6	hrs
Front - Zone 3 Temperature	380 - 400	°C
Middle - Zone 2 Temperature	380 - 400	°C
Rear - Zone 1 Temperature	370 - 380	°C
Mold Temperature	175 - 190	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	60 - 100	rpm