



LNP™ THERMOCOMP™ Compound LF008

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound LF-1008

Product reorder name: LF008

LNP THERMOCOMP LF008 is a compound based on Polyetheretherketone resin containing 40% Glass Fiber.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield	20	kgf/cm ²	ASTM D 638
Tensile Stress, break	1570	kgf/cm ²	ASTM D 638
Tensile Strain, yield	2.4	%	ASTM D 638
Tensile Strain, break	2.4	%	ASTM D 638
Tensile Modulus, 5 mm/min	140600	kgf/cm ²	ASTM D 638
Flexural Stress	2390	kgf/cm ²	ASTM D 790
Flexural Modulus	98400	kgf/cm ²	ASTM D 790
Tensile Stress, yield	156	MPa	ISO 527
Tensile Stress, break	155	MPa	ISO 527
Tensile Strain, yield	2.2	%	ISO 527
Tensile Strain, break	2.4	%	ISO 527
Tensile Modulus, 1 mm/min	12810	MPa	ISO 527
Flexural Stress	240	MPa	ISO 178
Flexural Modulus	10400	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	82	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	7	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	138	cm-kgf	ASTM D 3763
Multiaxial Impact	37	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	53	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
THERMAL			
CTE, -40°C to 40°C, flow	1.74E-05	1/°C	ASTM E 831



LNP™ THERMOCOMP™ Compound LF008

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -40°C to 40°C, xflow	4.18E-05	1/°C	ASTM E 831
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	261	°C	ISO 75/Af
PHYSICAL			
Density	1.61	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs (5)	0.5 - 0.7	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1 - 3	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.64	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	1.1	%	ISO 294
Density	1.61	g/cm ³	ISO 1183



LNP™ THERMOCOMP™ Compound LF008

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	150	°C
Drying Time	4 - 6	hrs
Front - Zone 3 Temperature	380 - 400	°C
Middle - Zone 2 Temperature	380 - 400	°C
Rear - Zone 1 Temperature	370 - 380	°C
Mold Temperature	175 - 190	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	60 - 100	rpm