

# SABIC<sup>®</sup> FORTIFY<sup>™</sup> C0570

## POLYOLEFIN ELASTOMER

## **DESCRIPTION**

 $SABIC^{\$}$  FORTIFY C0570 is an ethylene octene copolymer produced by solution polymerization using metallocene catalyst. This product is available as free flowing pellets.

SABIC<sup>®</sup> FORTIFY<sup>™</sup> C0570 is designed as a low density and high performance copolymer modifier to provide superior impact properties and flow characteristics.

### **TYPICAL APPLICATIONS**

Typical applications are impact modifier in thermoplastic olefin compounds, footwear midsoles and wire and cable extrusion.

### TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Density	868	kg/m³	ASTM D792
Melt Flow Rate			
at 190°C and 2.16 kg	0.5	g/10 min	ASTM D1238
at 230°C and 2.16 kg	0.9	g/10 min	ASTM D1238
Mooney viscosity (ML 1+4, 121 °C)	36	MU	ASTM D1646
MECHANICAL PROPERTIES (1)			
Tensile Properties			
100% modulus	3.1	MPa	ASTM D638
elongation	800	%	ASTM D638
strength at break	10.3	MPa	ASTM D638
Durometer Hardness			
shore A (1 second)	74	-	ASTM D2240
shore D (1 second)	23	-	ASTM D2240
Flexural Modulus (1% Secant)	15.2	MPa	ASTM D790 A
Tear Strength (Type C)	45.1	kN/m	ASTM D624
THERMAL PROPERTIES			
Peak Melting Temperature	59	°C	SABIC method
Glass Transition Temperature, Tg	-54	°C	SABIC method

<sup>(1)</sup>All physical properties were measured from specimens cut from compression molded. These typical values depend onmanufacturing conditions. Therefore, customers should confirm the product performance by using their own tests.