



LNP™ LUBRICOMP™ Compound BX02715

Americas: COMMERCIAL

Also known as: LNP™ LUBRICOMP™ Compound PDX-B-02715

Product reorder name: BX02715

LNP LUBRICOMP BX02715 is a compound based on SAN containing proprietary fillers. Added features of this grade include: Wear Resistant, Tight Dimensional Tolerance, Good for Water Meter Applications.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	610	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	1.1	%	ASTM D 638
Tensile Modulus, 5 mm/min	93600	kgf/cm ²	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	880	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	82500	kgf/cm ²	ASTM D 790
Tensile Stress, break, 5 mm/min	58	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1	%	ISO 527
Tensile Modulus, 1 mm/min	8460	MPa	ISO 527
Flexural Stress	71	MPa	ISO 178
Flexural Modulus, 2 mm/min	7970	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	8	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	1	cm-kgf/cm	ASTM D 256
Multiaxial Impact	9	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	31	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	6	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	1	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	101	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	96	°C	ASTM D 648
CTE, -30°C to 30°C, flow	3.9E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	4.5E-05	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	101	°C	ISO 75/Bf



LNP™ LUBRICOMP™ Compound BX02715

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	96	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.34	-	ASTM D 792
Density	1.35	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.11	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.2 - 0.4	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.3 - 0.5	%	ASTM D 955
Density	1.35	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62



LNP™ LUBRICOMP™ Compound BX02715

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Maximum Moisture Content	0.15	%
Melt Temperature	260	°C
Front - Zone 3 Temperature	275 - 290	°C
Middle - Zone 2 Temperature	245 - 255	°C
Rear - Zone 1 Temperature	205 - 215	°C
Mold Temperature	80 - 95	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm