



NORYL™ Resin N1150
Americas: COMMERCIAL

NORYL N1150 is an unfilled, injection moldable modified polyphenylene ether resin. Designed for good dimensional stability and good flow, this resin also uses non-chlorinated, non-brominated FR additives to achieve a V0 UL94 rating at 0.75 mm with a specific density of 1.11 g/cm³. NORYL 1150 may be an excellent material candidate for applications requiring electrically insulating properties, low moisture absorption, low warpage, and thin wall flame resistance.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	760	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	560	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	4	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	8	%	ASTM D 638
Tensile Modulus, 5 mm/min	27500	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	1190	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	31100	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 50 mm/min	72	MPa	ISO 527
Tensile Stress, break, 50 mm/min	52	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	3.5	%	ISO 527
Tensile Strain, break, 50 mm/min	7	%	ISO 527
Tensile Modulus, 1 mm/min	2650	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	105	MPa	ISO 178
Flexural Modulus, 2 mm/min	2600	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	8	cm-kgf/cm	ASTM D 256
Izod Impact, notched, -30°C	6	cm-kgf/cm	ASTM D 256
Instrumented Impact Total Energy, 23°C	407	cm-kgf	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	6	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	4	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	6	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	130	°C	ASTM D 1525



NORYL™ Resin N1150
Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	108	°C	ASTM D 648
CTE, -40°C to 40°C, flow	5.45E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	5.75E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	5.45E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	5.75E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	130	°C	ISO 306
Vicat Softening Temp, Rate B/120	132	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	109	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.11	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.5 - 0.7	%	SABIC Method
Melt Flow Rate, 280°C/5.0 kgf	15	g/10 min	ASTM D 1238
Density	1.11	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.07	%	ISO 62
Melt Volume Rate, MVR at 280°C/5.0 kg	15	cm ³ /10 min	ISO 1133
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating (3)	0.75	mm	UL 94



NORYL™ Resin N1150

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	95 - 100	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	260 - 290	°C
Nozzle Temperature	260 - 290	°C
Front - Zone 3 Temperature	250 - 290	°C
Middle - Zone 2 Temperature	240 - 280	°C
Rear - Zone 1 Temperature	225 - 275	°C
Mold Temperature	70 - 95	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	20 - 100	rpm
Shot to Cylinder Size	30 - 70	%
Vent Depth	0.038 - 0.051	mm