



NORYL™ Resin WCD891B

Americas: COMMERCIAL

Non-halogenated flame retardant, flexible NORYL resin intended for evaluation in wire and cable applications. Strong flame retardant performance capable of meeting VW-1 and 80°C end use temperature requirements as defined by UL 1581. 89 Shore A hardness. Good processing by using standard extrusion equipment. UL1581 tests conducted on 2.0 mm wire with 0.12 mm x 20 stranded copper conductor.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 50 mm/min	160	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	170	%	ASTM D 638
Flexural Modulus, 12.5 mm/min, 100 mm span	1600	kgf/cm ²	ASTM D 790
Hardness, Shore A, 30S reading	89	-	ASTM D 2240
Tensile Stress, break, 50 mm/min	15	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	140	%	ISO 527
Flexural Modulus, 12.5 mm/min	140	MPa	ISO 178
Tear strength	7	N/mm	ISO 6383
IMPACT			
Brittleness Temperature	<-40	°C	ASTM D 746
PHYSICAL			
Specific Gravity	1.1	-	ASTM D 792
Melt Flow Rate, 250°C/5.0 kgf	20	g/10 min	ASTM D 1238
ELECTRICAL			
Volume Resistivity	1.5E+15	Ohm-cm	ASTM D 257
Surface Resistivity	5.1E+15	Ohm	ASTM D 257
Dielectric strength in oil, 2.0mm	24	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	2.9	-	IEC 60250
Dissipation Factor, 1 MHz	0.04	-	IEC 60250
Comparative Tracking Index	600	V	IEC 60112
FLAME CHARACTERISTICS			
UL Compliant, 94V-0 Flame Class Rating (3)(4)	4	mm	UL 94 by SABIC-IP
Glow Wire Flammability Index 850°C, passes at	3	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 3.0 mm	750	°C	IEC 60695-2-13
Oxygen Index (LOI)	27	%	ISO 4589



NORYL™ Resin WCD891B

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
WIRE AND CABLE - UL 1581 tested on 2.0mm wire with 0.12mmx20 stranded copper			
Tensile strength @ break	18	MPa	UL 1581
Tensile elongation @ break	215	%	UL 1581
Tensile strength @ break after 7days @113°C	21	MPa	UL 1581
Tensile elongation @ break after 7days @113°C	160	%	UL 1581
UL temperature rating	80	°C	UL 1581
Heat Deformation at 100°C/250g	9	%	UL 1581
VW-1	Pass	-	UL 1581



NORYL™ Resin WCD891B

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Wire Coating Extrusion		
Drying Temperature	75 - 85	°C
Drying Time	5 - 7	hrs
Drying Time (Cumulative)	12	hrs
Maximum Moisture Content	0.02	%
Extruder Length/Diameter Ratio (L/D)	22:1 to 26:1	-
Screw Speed	15 - 85	rpm
Feed Zone Temperature	180 - 220	°C
Middle Zone Temperatures	220 - 250	°C
Head Zone Temperature	220 - 250	°C
Neck Temperature	220 - 250	°C
Cross-head Temperature	220 - 250	°C
Die Temperature	220 - 250	°C
Melt Temperature	220 - 250	°C
Conductor Pre-heat Temperature	25 - 120	°C
Screen Pack	150 - 100	-
Cooling Water Air Gap	100 - 200	mm
Water Bath Temperature	15 - 60	°C

• NOTE: Recommended Drying Parameters are based on usage of Dehumidify Drying / Drying Oven.