



Noryl GTX* Resin GTX8720

Europe-Africa-Middle East: COMMERCIAL

Noryl GTX* GTX8720 resin is a glass filled, high performance blend of PPE/PA that exhibits an excellent balance of high-heat resistance, strength, flow, and conductivity. This grade can be electro-statically painted or powder coated without the need for a conductive primer.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	140	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	140	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	3.1	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	4	%	ASTM D 638
Tensile Modulus, 5 mm/min	7000	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	200	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	6600	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	140	MPa	ISO 527
Tensile Stress, break, 5 mm/min	140	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3.1	%	ISO 527
Tensile Strain, break, 5 mm/min	4	%	ISO 527
Tensile Modulus, 1 mm/min	7000	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	200	MPa	ISO 178
Flexural Modulus, 2 mm/min	6600	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	85	J/m	ASTM D 256
Izod Impact, notched, -30°C	60	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	17	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	10	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	8	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	11	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	215	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	215	°C	ASTM D 648



Noryl GTX* Resin GTX8720

Europe-Africa-Middle East: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	215	°C	ASTM D 648
CTE, -40°C to 40°C, flow	2.3E+00	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.E+00	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	2.3E+00	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.E+00	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	215	°C	ISO 306
Vicat Softening Temp, Rate B/120	225	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	215	°C	ISO 75/Bf
PHYSICAL			
Specific Gravity	1.26	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.26 - 0.3	%	GE Method
Mold Shrinkage, xflow, 3.2 mm	0.72 - 0.85	%	GE Method
Melt Flow Rate, 280°C/5.0 kgf	8.6	g/10 min	ASTM D 1238
Density	1.26	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	4	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.5	%	ISO 62
Melt Volume Rate, MVR at 280°C/5.0 kg	7	cm ³ /10 min	ISO 1133
ELECTRICAL			
Volume Resistivity	1.E+03 - 1.E+04	Ohm-cm	GE Method



Noryl GTX* Resin GTX8720

Europe-Africa-Middle East: COMMERCIAL

• Do NOT mix NORYL GTX* resin with other grades of NORYL* resins.

PROCESSING PARAMETERS	TYPICAL VALUE	UNIT
Injection Molding		
Drying Temperature	95 - 105	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.07	%
Minimum Moisture Content	0.02	%
Melt Temperature	280 - 305	°C
Nozzle Temperature	280 - 305	°C
Front - Zone 3 Temperature	275 - 305	°C
Middle - Zone 2 Temperature	270 - 305	°C
Rear - Zone 1 Temperature	265 - 305	°C
Mold Temperature	75 - 120	°C
Back Pressure	0.3 - 1.4	MPa
Screw Speed	20 - 100	rpm
Shot to Cylinder Size	30 - 50	%
Vent Depth	0.013 - 0.038	mm

- Polystyrene and acrylic regrind are effective purging Materials. Use temperature range appropriate for particular purging resin.
- Regrind must also be dried. Maximum 25% regrind.
- Dry at recommended temperatures and times for optimum performance. Overdrying can cause loss of physical properties and/or create appearance defects. Do not exceed recommended basic drying time and temperature above or:
 - 4-8 hrs at 95°C (200°F), 10 hrs max
 - 6-12 hrs at 80°C (175°F), 16 hrs max
 - 8-16 hrs at 65°C (150°F), 24 hrs max
- AVOID air circulating tray ovens. Moisture levels in heated ambient air can exceed moisture level in the resin itself, causing moisture ABSORPTION not drying.
- Avoid melt temperature in excess of 300°C (575°F) and residence times over 6-8 minutes (may affect properties and/or appearance).
- Nozzle temperature controls assist in elimination of drool premature freeze-off.
- Shot sizes in excess of 50% barrel capacity can lead to difficulties in providing a consistent, homogenous plastic melt.