



LNP™ STAT-KON™ Compound ZEL34XXC

Europe-Africa-Middle East: COMMERCIAL

LNP STAT-KON ZEL34XXC is a compound based on PPE+PS Blend resin containing Carbon Fiber, PTFE. Added features include : Electrically Conductive , Internally Lubricated.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break, 5 mm/min	83	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.4	%	ISO 527
Tensile Modulus, 1 mm/min	10600	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	120	MPa	ISO 178
Flexural Modulus, 2 mm/min	8100	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	15	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	1.8E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	6.6E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	127	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	121	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow (5)	0.09	%	SABIC Method
Density	1.23	g/cm ³	ISO 1183
ELECTRICAL			
Surface Resistivity	1.E+02 - 1.E+04	Ohm	ASTM D 257



LNP™ STAT-KON™ Compound ZEL34XXC

Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Melt Temperature	300 - 305	°C
Front - Zone 3 Temperature	300 - 310	°C
Middle - Zone 2 Temperature	290 - 300	°C
Rear - Zone 1 Temperature	275 - 290	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm