

LNP* Thermocomp* Compound ZF-1006 BK8-950

Asia Pacific: COMMERCIAL

LNP* Thermocomp* ZF-1006 BK8-950 is a compound based on PPE+PS Blend resin containing Glass Fiber.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, break	1100	kgf/cm ²	ASTM D 638
Tensile Strain, break	1.6	%	ASTM D 638
Tensile Modulus, 50 mm/min	100600	kgf/cm ²	ASTM D 638
Flexural Stress	1680	kgf/cm ²	ASTM D 790
Flexural Modulus	90800	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	53	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	11	cm-kgf/cm	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	135	°C	ASTM D 648
PHYSICAL			
Density	1.31	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs	0.3	%	ASTM D 955