



NORYL™ Resin RN0401
Americas: COMMERCIAL

NORYL RN0401 resin is an unfilled Post Consumer Recycle (PCR) based injection moldable modified polyphenylene ether blend comprising at least 20% PCR content. Available in black only.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	560	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	400	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	3	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	15	%	ASTM D 638
Tensile Modulus, 5 mm/min	21400	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	810	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	25400	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 50 mm/min	50	MPa	ISO 527
Tensile Stress, break, 50 mm/min	35	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	3	%	ISO 527
Tensile Strain, break, 50 mm/min	15	%	ISO 527
Tensile Modulus, 1 mm/min	2200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	75	MPa	ISO 178
Flexural Modulus, 2 mm/min	2300	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	10	cm-kgf/cm	ASTM D 256
Izod Impact, notched 80*10*4 +23°C	9	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	70	°C	ASTM D 648
Vicat Softening Temp, Rate B/120	94	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	70	°C	ISO 75/Af
Relative Temp Index, Elec	65	°C	UL 746B
Relative Temp Index, Mech w/impact	65	°C	UL 746B



NORYL™ Resin RN0401

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
Relative Temp Index, Mech w/o impact	65	°C	UL 746B
PHYSICAL			
Specific Gravity	1.12	-	ASTM D 792
Melt Flow Rate, 260°C/5.0 kgf	30	g/10 min	ASTM D 1238
Density	1.11	g/cm ³	ISO 1183
Melt Volume Rate, MVR at 260°C/5.0 kg	30	cm ³ /10 min	ISO 1133
ELECTRICAL			
Dielectric Strength, in oil, 3.2 mm	25	kV/mm	ASTM D 149
Arc Resistance, Tungsten {PLC}	7	PLC Code	ASTM D 495
High Voltage Arc Track Rate {PLC}	3	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Compliant, 94V-0 Flame Class Rating (3)(4)	2	mm	UL 94 by SABIC-IP



NORYL™ Resin RN0401
Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	70 - 80	°C
Drying Time	2 - 4	hrs
Melt Temperature	240 - 270	°C
Mold Temperature	60 - 80	°C