



NORYL™ Resin PVX0901
Asia Pacific: COMMERCIAL

Multi purpose V1 grade

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	610	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	450	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	3.3	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	6.6	%	ASTM D 638
Tensile Modulus, 5 mm/min	25400	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	870	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	23400	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 50 mm/min	59	MPa	ISO 527
Tensile Stress, break, 50 mm/min	44	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	3.3	%	ISO 527
Tensile Strain, break, 50 mm/min	8.8	%	ISO 527
Tensile Modulus, 1 mm/min	2440	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	95	MPa	ISO 178
Flexural Modulus, 2 mm/min	2450	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	17	cm-kgf/cm	ASTM D 256
Izod Impact, notched, -30°C	8	cm-kgf/cm	ASTM D 256
Instrumented Impact Total Energy, 23°C	377	cm-kgf	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	13	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	10	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	12	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	116	°C	ASTM D 1525



NORYL™ Resin PVX0901
Asia Pacific: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	92	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	92	°C	ASTM D 648
CTE, -40°C to 40°C, flow	7.5E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.1E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	7.4E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.8E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	N/A	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	116	°C	ISO 306
Vicat Softening Temp, Rate B/120	109	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	89	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.1	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.5 - 0.7	%	SABIC Method
Melt Flow Rate, 280°C/5.0 kgf	50	g/10 min	ASTM D 1238
Density	1.1	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.24	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.04	%	ISO 62
Melt Volume Rate, MVR at 280°C/5.0 kg	52	cm ³ /10 min	ISO 1133
FLAME CHARACTERISTICS			
UL Compliant, 94V-1 Flame Class Rating (3)(4)	1.5	mm	UL 94 by SABIC-IP



NORYL™ Resin PVX0901

Asia Pacific: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	75 - 80	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	250 - 275	°C
Nozzle Temperature	250 - 275	°C
Front - Zone 3 Temperature	240 - 275	°C
Middle - Zone 2 Temperature	225 - 270	°C
Rear - Zone 1 Temperature	215 - 265	°C
Mold Temperature	55 - 75	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	20 - 100	rpm
Shot to Cylinder Size	30 - 70	%
Vent Depth	0.038 - 0.051	mm