



LNP™ THERMOCOMP™ Compound ZF0089

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound ZF-1008 EP FR

Product reorder name: ZF0089

LNP THERMOCOMP ZF0089 is a compound based on PPO resin containing 40% Glass Fiber. Added features of this material include: Exceptional Processing, Flame Retardant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	1020	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	1	%	ASTM D 638
Tensile Modulus, 50 mm/min	132700	kgf/cm ²	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	1330	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	120300	kgf/cm ²	ASTM D 790
Tensile Stress, break, 5 mm/min	8	MPa	ISO 527
Tensile Strain, break, 5 mm/min	0.8	%	ISO 527
Tensile Modulus, 1 mm/min	12280	MPa	ISO 527
Flexural Modulus, 2 mm/min	11940	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	33	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	7	cm-kgf/cm	ASTM D 256
Multiaxial Impact	30	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	125	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	19	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	110	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	103	°C	ASTM D 648
CTE, -30°C to 30°C, flow	3.07E+01	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	5.37E+01	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	112	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	105	°C	ISO 75/Af



LNP™ THERMOCOMP™ Compound ZF0089

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
PHYSICAL			
Specific Gravity	1.52	-	ASTM D 792
Density	1.52	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.07	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.2 - 0.5	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.5 - 0.8	%	ASTM D 955
Density	1.51	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.09	%	ISO 62



LNP™ THERMOCOMP™ Compound ZF0089

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Melt Temperature	300 - 305	°C
Front - Zone 3 Temperature	300 - 310	°C
Middle - Zone 2 Temperature	290 - 300	°C
Rear - Zone 1 Temperature	275 - 290	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm