



NORYL™ Resin WCD933
Americas: COMMERCIAL

Flexible and non-halogenated flame retardant extrusion grade intended for evaluation in applications such as insulation of HD 21.14 flexible cables. Flame retardant performance capable of meeting EN 50265-2-1 requirement. 93 Shore A hardness. Processing typically conducted on standard extrusion equipment. Wire tests conducted on 2.0 mm wire with 0.12 mm x 20 stranded copper conductor.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 50 mm/min	90	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	130	%	ASTM D 638
Flexural Modulus, 12.5 mm/min, 100 mm span	1600	kgf/cm ²	ASTM D 790
Hardness, Shore A, 30S reading	93	-	ASTM D 2240
Tensile Stress, break, 50 mm/min	9	MPa	ISO 527
Tensile Strain, break, 50 mm/min	175	%	ISO 527
Flexural Modulus, 12.5 mm/min	130	MPa	ISO 178
IMPACT			
Brittleness Temperature	<-40	°C	ASTM D 746
PHYSICAL			
Specific Gravity	1.33	-	ASTM D 792
Melt Flow Rate, 250°C/10.0 kgf	8.5	g/10 min	ASTM D 1238
ELECTRICAL			
Volume Resistivity	2.E+15	Ohm-cm	ASTM D 257
Relative Permittivity, 1 MHz	3	-	ASTM D 150
Dissipation Factor, 1 MHz	0.001	-	ASTM D 150
Dielectric strength in oil, 2.0mm	22.9	kV/mm	IEC 60243-1
Comparative Tracking Index	600	V	IEC 60112
FLAME CHARACTERISTICS			
Smoke Density on 0.5mm plaque, Non-flame, Ds, max	152	-	ASTM E 662
Smoke Density on 0.5mm plaque, Flame, Ds, max	56	-	ASTM E 662
Glow Wire Flammability Index 750°C, passes at	3	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 3.0 mm	775	°C	IEC 60695-2-13
Oxygen Index (LOI)	29	%	ISO 4589
WIRE AND CABLE - UL 1581 tested on 2.0mm wire with 0.12mmx20 stranded copper			
Tensile strength @ break	15	MPa	UL 1581



NORYL™ Resin WCD933

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
WIRE AND CABLE - UL 1581 tested on 2.0mm wire with 0.12mmx20 stranded copper			
Tensile elongation @ break	306	%	UL 1581
Tensile strength @ break after 7days @80°C	15	MPa	UL 1581
Tensile elongation @ break after 7days @80°C	267	%	UL 1581
Heat Deformation at 100°C/250g	10	%	UL 1581
Vertical Flame Test	PASSES	-	EN 50265-2-1



NORYL™ Resin WCD933

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Wire Coating Extrusion		
Drying Temperature	75 - 85	°C
Drying Time	5 - 7	hrs
Drying Time (Cumulative)	12	hrs
Maximum Moisture Content	0.02	%
Extruder Length/Diameter Ratio (L/D)	22:1 to 26:1	-
Screw Speed	15 - 85	rpm
Feed Zone Temperature	180 - 220	°C
Middle Zone Temperatures	220 - 250	°C
Head Zone Temperature	220 - 250	°C
Neck Temperature	220 - 250	°C
Cross-head Temperature	220 - 250	°C
Die Temperature	220 - 250	°C
Melt Temperature	220 - 250	°C
Conductor Pre-heat Temperature	25 - 120	°C
Screen Pack	150 - 100	-
Cooling Water Air Gap	100 - 200	mm
Water Bath Temperature	15 - 60	°C

• NOTE: Recommended Drying Parameters are based on usage of Dehumidify Drying / Drying Oven.