



## LNP™ STAT-KON™ Compound CD000I

### Americas: COMMERCIAL

Also known as: LNP™ STAT-KON™ Compound C-HI

Product reorder name: CD000I

LNP STAT-KON CD000I is a compound based on Polystyrene resin containing Carbon Powder. Added features of this material include: Electrically Conductive, High Impact.

| TYPICAL PROPERTIES <sup>1</sup>              | TYPICAL VALUE | Unit                | Standard    |
|----------------------------------------------|---------------|---------------------|-------------|
| <b>MECHANICAL</b>                            |               |                     |             |
| Tensile Stress, yld, Type I, 5 mm/min        | 230           | kgf/cm <sup>2</sup> | ASTM D 638  |
| Tensile Stress, brk, Type I, 5 mm/min        | 160           | kgf/cm <sup>2</sup> | ASTM D 638  |
| Tensile Strain, yld, Type I, 5 mm/min        | 1.2           | %                   | ASTM D 638  |
| Tensile Strain, brk, Type I, 5 mm/min        | 9.7           | %                   | ASTM D 638  |
| Tensile Modulus, 5 mm/min                    | 23200         | kgf/cm <sup>2</sup> | ASTM D 638  |
| Flexural Stress, yld, 1.3 mm/min, 50 mm span | 430           | kgf/cm <sup>2</sup> | ASTM D 790  |
| Flexural Modulus, 1.3 mm/min, 50 mm span     | 23200         | kgf/cm <sup>2</sup> | ASTM D 790  |
| Tensile Stress, yield, 5 mm/min              | 23            | MPa                 | ISO 527     |
| Tensile Stress, break, 5 mm/min              | 17            | MPa                 | ISO 527     |
| Tensile Strain, yield, 5 mm/min              | 1.2           | %                   | ISO 527     |
| Tensile Strain, break, 5 mm/min              | 7.1           | %                   | ISO 527     |
| Tensile Modulus, 1 mm/min                    | 2120          | MPa                 | ISO 527     |
| Flexural Stress                              | 40            | MPa                 | ISO 178     |
| Flexural Modulus, 2 mm/min                   | 2100          | MPa                 | ISO 178     |
| <b>IMPACT</b>                                |               |                     |             |
| Izod Impact, unnotched, 23°C                 | 75            | cm-kgf/cm           | ASTM D 4812 |
| Izod Impact, notched, 23°C                   | 8             | cm-kgf/cm           | ASTM D 256  |
| Multiaxial Impact                            | 157           | cm-kgf              | ISO 6603    |
| Instrumented Impact Total Energy, 23°C       | 190           | cm-kgf              | ASTM D 3763 |
| Izod Impact, unnotched 80*10*4 +23°C         | 31            | kJ/m <sup>2</sup>   | ISO 180/1U  |
| Izod Impact, notched 80*10*4 +23°C           | 5             | kJ/m <sup>2</sup>   | ISO 180/1A  |
| <b>THERMAL</b>                               |               |                     |             |
| HDT, 0.45 MPa, 3.2 mm, unannealed            | 87            | °C                  | ASTM D 648  |



## LNP™ STAT-KON™ Compound CD000I

Americas: COMMERCIAL

| TYPICAL PROPERTIES <sup>1</sup>        | TYPICAL VALUE   | Unit              | Standard   |
|----------------------------------------|-----------------|-------------------|------------|
| <b>THERMAL</b>                         |                 |                   |            |
| HDT, 1.82 MPa, 3.2mm, unannealed       | 75              | °C                | ASTM D 648 |
| CTE, -40°C to 40°C, flow               | 9.8E-05         | 1/°C              | ASTM E 831 |
| CTE, -40°C to 40°C, xflow              | 1.07E-04        | 1/°C              | ASTM E 831 |
| HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm | 87              | °C                | ISO 75/Bf  |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm  | 78              | °C                | ISO 75/Af  |
| <b>PHYSICAL</b>                        |                 |                   |            |
| Specific Gravity                       | 1.08            | -                 | ASTM D 792 |
| Density                                | 1.08            | g/cm <sup>3</sup> | ASTM D 792 |
| Moisture Absorption, 50% RH, 24 hrs    | 0.1             | %                 | ASTM D 570 |
| Mold Shrinkage, flow, 24 hrs (5)       | 0.3 - 0.7       | %                 | ASTM D 955 |
| Mold Shrinkage, xflow, 24 hrs (5)      | 0.4 - 0.7       | %                 | ASTM D 955 |
| Moisture Absorption (23°C / 50% RH)    | 0.13            | %                 | ISO 62     |
| <b>ELECTRICAL</b>                      |                 |                   |            |
| Surface Resistivity                    | 3.E+00 - 5.E+00 | Ohm               | ASTM D 257 |



## LNP™ STAT-KON™ Compound CD000I

### Americas: COMMERCIAL

| PROCESSING PARAMETERS       | TYPICAL VALUE | Unit |
|-----------------------------|---------------|------|
| <b>Injection Molding</b>    |               |      |
| Drying Temperature          | 80            | °C   |
| Drying Time                 | 4             | hrs  |
| Melt Temperature            | 250           | °C   |
| Front - Zone 3 Temperature  | 265 - 275     | °C   |
| Middle - Zone 2 Temperature | 245 - 255     | °C   |
| Rear - Zone 1 Temperature   | 220 - 230     | °C   |
| Mold Temperature            | 40 - 65       | °C   |
| Back Pressure               | 0.2 - 0.3     | MPa  |
| Screw Speed                 | 30 - 60       | rpm  |