

DESCRIPTION

The performance of this compound has been optimized for improved impact resistance.

GENERAL PROPERTIES	VALUE	UNIT	TEST STANDARD
Filler Content	0	%	ISO 3451/1
Density	0.91	g/cm ³	ISO 1183A
Melt Flow	5	g/10 min	ISO 1133

MECHANICAL PROPERTIES	VALUE	UNIT	TEST STANDARD
Tensile Strength	28	MPa	ISO 527
Flexural Strength	38	MPa	ISO 178
Flexural Modulus	1300	MPa	ISO 178
Charpy Notched 23°C	10	kJ/m ²	ISO 179

THERMAL PROPERTIES	VALUE	UNIT	TEST STANDARD
HDT @ 1.8 MPa	53	°C	ISO 75

Auto Approvals

n/a

