

DESCRIPTION:

This compound has been heat stabilized for higher temperature applications.

GENERAL PROPERTIES	VALUE	UNIT	TEST STANDARD
Glass Reinforcement	20	%	ASTM D5630
Specific Gravity	1.05	g/cm ³	ASTM D792 / ISO 1183A
Melt Flow	2	g/10 min	ASTM D1238

MECHANICAL PROPERTIES	VALUE	UNIT	TEST STANDARD
Flexural Strength	101	MPa	ASTM D790
Flexural Modulus - Tangent	3757	MPa	ASTM D790
Notched Izod - ASTM Flex Bar 23C	96	J/m	ASTM D256

