

**DESCRIPTION:**

This compound has been heat stabilized for higher temperature applications.

| GENERAL PROPERTIES  | VALUE | UNIT              | TEST STANDARD         |
|---------------------|-------|-------------------|-----------------------|
| Glass Reinforcement | 20    | %                 | ASTM D5630            |
| Specific Gravity    | 1.05  | g/cm <sup>3</sup> | ASTM D792 / ISO 1183A |
| Melt Flow           | 2     | g/10 min          | ASTM D1238            |

| MECHANICAL PROPERTIES            | VALUE | UNIT | TEST STANDARD |
|----------------------------------|-------|------|---------------|
| Flexural Strength                | 101   | MPa  | ASTM D790     |
| Flexural Modulus - Tangent       | 3757  | MPa  | ASTM D790     |
| Notched Izod - ASTM Flex Bar 23C | 96    | J/m  | ASTM D256     |

