

DESCRIPTION

This is a high-flow Thermoplastic Olefin (TPO) compound that is designed for interior trim applications requiring good scratch/mar performance.

GENERAL PROPERTIES	VALUE	UNIT	TEST STANDARD
Density	0.99	g/cm ³	ISO 1183A
Melt Flow	28	g/10 min	ISO 1133

MECHANICAL PROPERTIES	VALUE	UNIT	TEST STANDARD
Tensile Strength	18	MPa	ISO 527
Flexural Modulus	1600	MPa	ISO 178
Charpy Notched, 23°C	30	kJ/m ²	ISO 179
Charpy Notched, -30°C	3.5	kJ/m ²	ISO 179

THERMAL PROPERTIES	VALUE	UNIT	TEST STANDARD
HDT	51	°C	ISO 75

