

DESCRIPTION

This general purpose polypropylene compound has been heat stabilized for underhood applications. It is very suitable for good processability in thin-walled or large applications.

GENERAL PROPERTIES	VALUE	UNIT	TEST STANDARD
Filler Content	30	%	ISO 3451/1
Density	1.13	g/cm ³	ISO 1183A
Melt Flow	14	g/10 min	ISO 1133

MECHANICAL PROPERTIES	VALUE	UNIT	TEST STANDARD
Tensile Strength	85	MPa	ISO 527
Flexural Strength	132	MPa	ISO 178
Flexural Modulus	6000	MPa	ISO 178
Charpy Notched 23°C	9	kJ/m ²	ISO 179

THERMAL PROPERTIES	VALUE	UNIT	TEST STANDARD
HDT @ 1.8 MPa	148	°C	ISO 75

Auto Approvals
 GM GMW16607P-PP-GF30
 FCA MS-DB500 CPN 4602

