

DESCRIPTION

This general purpose compound is designed for high strength and stiffness. Additionally, it has been heat stabilized for higher temperature applications.

GENERAL PROPERTIES	VALUE	UNIT	TEST STANDARD
Filler Content	40	%	ISO 3451/1
Density	1.24	g/cm ³	ISO 1183A
Melt Flow	4	g/10 min	ISO 1133

MECHANICAL PROPERTIES	VALUE	UNIT	TEST STANDARD
Tensile Strength	88	MPa	ISO 527
Flexural Strength	134	MPa	ISO 178
Flexural Modulus	7600	MPa	ISO 178
Charpy Notched 23°C	10	kJ/m ²	ISO 179

THERMAL PROPERTIES	VALUE	UNIT	TEST STANDARD
HDT @ 1.8 MPa	144	°C	ISO 75

Auto Approvals

GM GMW16607P-PP-GF40
 FCA MS-DB500 CPN 4757

