

DESCRIPTION

This is a high-flow Thermoplastic Olefin (TPO) compound that is designed for interior trim applications requiring good scratch/mar performance.

GENERAL PROPERTIES	VALUE	UNIT	TEST STANDARD
Density	0.99	g/cm ³	ISO 1183A
Melt Flow	20	g/10 min	ISO 1133
MECHANICAL PROPERTIES	VALUE	UNIT	TEST STANDARD
Tensile Strength	16	MPa	ISO 527
Flexural Modulus	1800	MPa	ISO 178
Charpy Notched, 23°C	38	kJ/m ²	ISO 179
Charpy Notched, -30°C	4.5	kJ/m ²	ISO 179
THERMAL PROPERTIES	VALUE	UNIT	TEST STANDARD
HDT	52	°C	ISO 75

