

XYRON™ 1000H

Asahi Kasei Corporation - Polyphenylene Ether + PS

General Information

Product Description

Modified PPE
Unreinforced non-Flame retardant
Heat resistance High

General

Processing Method • Injection Molding
Part Marking Code (ISO11469) (ISO 11469) • >PPE+PS<

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.07	g/cm ³	ISO 1183
Molding Shrinkage ² (2.00 mm)	0.70 to 0.80	%	Internal Method
Water Absorption (24 hr, 23°C)	0.060	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	70.0	MPa	ISO 527
Nominal Tensile Strain at Break (23°C)	24	%	ISO 527
Flexural Modulus (23°C)	2400	MPa	ISO 178
Flexural Stress (23°C)	112	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ³ (23°C)	8.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed	158	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow : -30 to 65°C	6.0E-5	cm/cm/°C	
Transverse : -30 to 65°C	6.2E-5	cm/cm/°C	
Heat Deflection Temperature - (1.8MPa, Unannealed)	170	°C	ASTM D648



XYRON™ 1000H

Asahi Kasei Corporation - Polyphenylene Ether + PS

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+16	ohms·cm	IEC 60093
Dielectric Constant			IEC 60250
100 Hz	2.80		
1 MHz	2.80		
Dissipation Factor			IEC 60250
100 Hz	5.0E-4		
1 MHz	6.0E-4		

Processing Information		
Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	100 to 120	°C
Drying Time - Hot Air Dryer	2.0 to 4.0	hr
Processing (Melt) Temp	280 to 320	°C
Mold Temperature	80 to 120	°C

Notes

- ¹ Typical properties: these are not to be construed as specifications.

² 150x150x2 mm

³ 4 mm

