

XYRON™ WG720

Asahi Kasei Corporation - Polyphenylene Ether + PS

General Information

Product Description

Modified PPE
20% Filler reinforced Non-Flame retardant
Please contact us for drinking water standards information.

General

Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight
Processing Method	• Injection Molding
Part Marking Code (ISO11469) (ISO 11469)	• >PPE+PS-GF20<

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.21	g/cm ³	ISO 1183
Molding Shrinkage ² (2.00 mm)	0.26 to 0.54	%	Internal Method
Water Absorption (24 hr, 23°C)	0.060	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	105	MPa	ISO 527
Tensile Strain (Break, 23°C)	2.0	%	ISO 527
Flexural Modulus (23°C)	6500	MPa	ISO 178
Flexural Stress (23°C)	164	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ³ (23°C)	10	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed	136	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow : -30 to 65°C	2.7E-5	cm/cm/°C	
Transverse : -30 to 65°C	6.9E-5	cm/cm/°C	
Heat Deflection Temperature - (1.8MPa, Unannealed)	140	°C	ASTM D648



XYRON™ WG720

Asahi Kasei Corporation - Polyphenylene Ether + PS

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+16	ohms·cm	IEC 60093
Dielectric Constant			IEC 60250
100 Hz	3.10		
1 MHz	3.10		
Dissipation Factor			IEC 60250
100 Hz	6.0E-4		
1 MHz	1.1E-3		
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.5 mm, ALL)	HB		UL 94

Processing Information			
Injection	Nominal Value	Unit	
Drying Temperature	90 to 100	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	260 to 300	°C	
Mold Temperature	60 to 100	°C	

Notes

- ¹ Typical properties: these are not to be construed as specifications.
- ² 150x150x2 mm
- ³ 4 mm

