

XYRON™ WG732

Asahi Kasei Corporation - Polyphenylene Ether + PS

General Information

Product Description

Modified PPE
30% Filler reinforced Non-Flame retardant
Drinking water standard compliance: NSF, KTW-BWGL, ACS, WRAS

General

Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Agency Ratings	• ACS DGS/VS 4 n° 2000-232 • DVGW W270	• KTW Guidelines • NSF STD-61	• WRAS BS6920-1: 2000 and 2014
Processing Method	• Injection Molding		
Part Marking Code (ISO11469) (ISO 11469)	• >PPE+PS-GF20<		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.28	g/cm ³	ISO 1183
Molding Shrinkage ² (2.00 mm)	0.20 to 0.50	%	Internal Method
Water Absorption (24 hr, 23°C)	0.060	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	140	MPa	ISO 527
Tensile Strain (Break, 23°C)	2.0	%	ISO 527
Flexural Modulus (23°C)	8900	MPa	ISO 178
Flexural Stress (23°C)	216	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ³ (23°C)	12	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed	144	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow : -30 to 65°C	2.3E-5	cm/cm/°C	
Transverse : -30 to 65°C	6.4E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+16	ohms·cm	IEC 60093



XYRON™ WG732

Asahi Kasei Corporation - Polyphenylene Ether + PS

Processing Information		
Injection	Nominal Value	Unit
Drying Temperature	90 to 100	°C
Drying Time	2.0 to 4.0	hr
Processing (Melt) Temp	260 to 300	°C
Mold Temperature	60 to 100	°C

Notes

- ¹ Typical properties: these are not to be construed as specifications.
- ² 150x150x2 mm
- ³ 4 mm

