

TENAC™-C 7590

Asahi Kasei Corporation - Acetal (POM) Copolymer

General Information

General			
Features	- Copolymer - Food Contact Acceptable	- High Flow - Low Viscosity	
Uses	Non-specific Food Applications		
Agency Ratings	EU 10/2011	FDA 21 CFR 177.2470	NSF STD-61
Processing Method	Injection Molding		
Part Marking Code (ISO11469) (ISO 11469)	>POM<		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	30	g/10 min	ISO 1133
Molding Shrinkage - Flow	1.6 to 2.0	%	Internal Method
Water Absorption (24 hr, 23°C, 50% RH)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2800	MPa	ISO 527-1
Tensile Stress (Yield)	64.0	MPa	ISO 527-2
Tensile Strain (Break)	30	%	ISO 527-2
Flexural Modulus	2600	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed	100	°C	ISO 75-2/A
CLTE - Flow	1.0E-4	cm/cm/°C	ISO 11359-2
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.75 mm)	HB		UL 94

Notes

¹ Typical properties: these are not to be construed as specifications.

