

TENAC™-C 5520

Asahi Kasei Corporation - Acetal (POM) Copolymer

General Information

General		
Uses	- Engineering Parts - Gears	- General Purpose - Housings
Part Marking Code (ISO11469) (ISO 11469)	• >POM<	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.41	g/cm ³	ASTM D792 ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	15	g/10 min	ISO 1133
Molding Shrinkage - Flow	1.6 to 2.0	%	Internal Method
Water Absorption (24 hr, 23°C, 50% RH)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2700	MPa	ISO 527-1
Tensile Stress			
Yield	63.0	MPa	ISO 527-2
--	63.0	MPa	ASTM D638
Tensile Elongation			
Break	35	%	ASTM D638
Break	33	%	ISO 527-2
Flexural Modulus			
--	2600	MPa	ASTM D790
--	2500	MPa	ISO 178
Flexural Strength	91.0	MPa	ASTM D790
Taber Abrasion Resistance	14.0	mg	ASTM D1044
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	6.0	kJ/m ²	ISO 179
Notched Izod Impact	61	J/m	ASTM D256



TENAC™-C 5520

Asahi Kasei Corporation - Acetal (POM) Copolymer

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	80		
R-Scale	115		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	158	°C	ASTM D648
0.45 MPa, Unannealed	156	°C	ISO 75-2/B
1.8 MPa, Unannealed	110	°C	ASTM D648
1.8 MPa, Unannealed	100	°C	ISO 75-2/A
CLTE - Flow	1.0E-4	cm/cm/°C	ASTM D696 ISO 11359-2
Specific Heat	1470	J/kg/°C	
Thermal Conductivity	0.23	W/m/K	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16 to 1.0E+17	ohms	ASTM D257
Volume Resistivity (23°C)	1.0E+15 to 1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	19	kV/mm	ASTM D149
Dielectric Constant (23°C, 1 MHz)	3.90		ASTM D150
Dissipation Factor (23°C, 1 MHz)	8.0E-3		ASTM D150
Arc Resistance	250	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.75 mm	HB		
1.5 mm	HB		

Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	80 to 90	°C
Drying Time - Hot Air Dryer	3.0 to 4.0	hr
Processing (Melt) Temp	180 to 210	°C
Mold Temperature	> 60	°C

Notes

¹ Typical properties: these are not to be construed as specifications.

