

TENAC™-C NS556

Asahi Kasei Corporation - Acetal (POM) Copolymer

General Information

General			
Filler / Reinforcement	• Mineral, 30% Filler by Weight		
Features AKEP website	• Dimensional Stability, Good	• Warpage, Low	
Uses	• Engineering Parts	• Gears	• Housings
Part Marking Code (ISO11469) (ISO 11469)	• >POM-MD30<		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.62	g/cm ³	ASTM D792 ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	9.0	g/10 min	ISO 1133
Molding Shrinkage - Flow	1.4 to 1.8	%	Internal Method
Water Absorption (24 hr, 23°C, 50% RH)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4300	MPa	ISO 527-1
Tensile Stress (Yield)	43.0	MPa	ISO 527-2
Tensile Elongation (Break)	25	%	ISO 527-2
Flexural Modulus	4100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	6.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed	124	°C	ISO 75-2/A
CLTE - Flow	1.0E-4	cm/cm/°C	ISO 11359-2
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.75 mm)	HB		UL 94



TENAC™-C NS556

Asahi Kasei Corporation - Acetal (POM) Copolymer

Processing Information		
Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	80 to 90	°C
Drying Time - Hot Air Dryer	3.0 to 4.0	hr
Processing (Melt) Temp	180 to 210	°C
Mold Temperature	> 60	°C

Notes

¹ Typical properties: these are not to be construed as specifications.

