

XYRON™ A0210

Asahi Kasei Corporation - Polyamide + PPE

General Information

Product Description

Modified PPE
PA/PPE alloy
Non-reinforced Non-Flame retardant
Easy FLOW

General

Features AKEP website	• Flow, High
Processing Method	• Injection Molding
Part Marking Code (ISO11469) (ISO 11469)	• >PA66+PPE<

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.11	g/cm ³	ISO 1183
Molding Shrinkage ² (3.00 mm)	1.3	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	65.0	MPa	ISO 527
Tensile Strain (Break, 23°C)	42	%	ISO 527
Flexural Modulus (23°C)	2500	MPa	ISO 178
Flexural Stress (23°C)	97.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ³ (23°C)	21	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 0.45 MPa, Unannealed	176	°C	ISO 75-2/B
CLTE			ISO 11359-2
Flow : -30 to 65°C	8.5E-5	cm/cm/°C	
Transverse : -30 to 65°C	9.3E-5	cm/cm/°C	



XYRON™ A0210

Asahi Kasei Corporation - Polyamide + PPE

Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (23°C)	2.1E+15	ohms·cm	IEC 60093
Dielectric Constant			IEC 60250
100 Hz	3.20		
1 MHz	3.00		
Dissipation Factor			IEC 60250
100 Hz	7.0E-3		
1 MHz	0.012		

Processing Information		
Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	110 to 130	°C
Drying Time - Hot Air Dryer	2.0 to 3.0	hr
Processing (Melt) Temp	280 to 300	°C
Mold Temperature	60 to 120	°C

Injection Notes

Recommended processing (melt) temperature of XYRON™ Polyamide + PPE is 280-300°C. Lower temperatures may lead to local degradation in properties due to non-uniform plasticization, while higher temperatures tend to cause silver streaking, other appearance problems and decomposition.

- Notes**
- ¹ Typical properties: these are not to be construed as specifications.

² 120x80x3 mm

³ 4 mm

