



扫一扫上面的二维码图案，加我为朋友。

Polyethylene HE1344

Compound for Cellular insulation of Communication cables

Description

HE1344

It is a fully formulated compound for chemical foamed data cable insulation. HE1344 is a high-density polyethylene compound containing chemical blowing agent.

Applications

HE1344 is intended for:

Foam or foam-skin insulation for telephone singles and data cable with typical expansion of 35-40%.

Dry core and petroleum jelly filled cables

Specifications

HE1344 meets the following material classification:

ISO 1872-PE, KEGHN, 45-D006 ¹

ASTM D1248 Type III, Class A, Category 4 ¹

¹ Refers to Base Resin

The following cable material standards are met by HE1344:

EN 50290-2-23

Cables manufactured with HE1344 using sound extrusion practice normally comply with the following cable product standards:

IEC 60708
IEC 61156

EN 50288
EN 50407

Special features

HE1344 consists of specially selected components to offer:

Consistent cell structure
Excellent extrusion stability
Good surface finish

use in petroleum filled cables when extruded with relative low expansion (<40%)

Physical Properties

| Property | Typical Value | Test Method |
|--|-----------------------------|-------------|
| Data should not be used for specification work | | |
| Density (Base Resin) | 943 kg/m ³ | ISO 1183 |
| Density (Compound) | 945 kg/m ³ | ISO 1183 |
| Bulk density | 500 - 600 kg/m ³ | |

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168





扫一扫上面的二维码图案，加我为朋友。

Polyethylene HE1344

Tensile Strain at Break (50 mm/min)
Tensile Strength (50 mm/min)

600 %
23 MPa

ISO 527
ISO 527

For information on the influence of petroleum jelly please refer to the article published on borealisgroup.com : "Impact of Petroleum Jelly on the Ageing of Telephone Wire", by going to the following link
http://www.borealisgroup.com/pdf/literature/borealis/technical-article/1112Impact_of_Petroleum_Jelly_on_the_Ageing_of_Telephone_Wire_Final.pdf

Physical Properties of expanded (45 %) insulation

| Property | Typical Value | Test Method |
|--|---------------|---------------|
| Data should not be used for specification work | | |
| Tensile Strength (50 mm/min), | 13 MPa | IEC 60811-501 |
| Tensile Strain (50 mm/min), | 500 % | IEC 60811-501 |
| Oxidation Induction Time (200 °C), | 50 min | IEC 60811-410 |
| Resistance to Thermal Ageing (105 °C) | 1.500 h | IEC 60811-408 |

Electrical Properties

| Property | Typical Value | Test Method |
|--|---------------|-------------|
| Data should not be used for specification work | | |
| Dielectric constant (1 MHz) ¹ | 2,33 | IEC 60250 |
| Dissipation Factor (1 MHz) ¹ | 0,0004 | IEC 60250 |

¹ Measured on moulded plaques containing blowing agent but not expanded

Processing Techniques

HE1344 can be processed over a wide range of conditions.

The adoption of correct processing conditions is important to obtain the optimum physical and electrical properties of the insulated wire. The melt temperature depends on the desired capacitance. The melt temperature should be kept within a close tolerance within +/- 1°C.

Conductor preheating is important for the insulation mechanical properties and to ensure good adhesion to the conductor. Heated water (up to 50°C) in the first cooling trough has been found beneficial to improve conductor adhesion.

Tooling

Pressure tooling is invariably required. The die diameter is a function of the level of expansion with a greater expansion requiring a smaller die. Typically die diameters 3 to 7% below the nominal insulation outer diameter are used.

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168



扫一扫上面的二维码图案，加我为朋友。

Polyethylene HE1344

Extrusion

| | |
|----------------------|--------------|
| Conductor preheating | 110 - 120 °C |
| Adapter | 195 °C |
| Barrel 1 | 155 °C |
| Barrel 2 | 170 °C |
| Barrel 3 | 185 °C |
| Barrel 4 | 195 °C |
| Die | 195 °C |
| Melt temperature | 195 - 200 °C |

Please contact your local Borealis representative for specific assistance.

Packaging

| | |
|----------|----------|
| Package: | Bags |
| | Octabins |
| | Bulk |

Storage

HE1344 should be stored in dry conditions at temperatures below 50°C and protected from UV-light.

Safety

The product is not classified as dangerous and is intended for industrial use only. Check and follow local codes and regulations!

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168



Polyethylene HE1344



扫一扫上面的二维码图案，加我为朋友。

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168