

Polyethylene CG8410



扫一扫上面的二维码图案，加我为朋友。

Description

CG8410 is a high-density polyethylene for extrusion coating.

Applications

CG8410 is designed for:

Extrusion coating of high volume production of boards and papers

Special features

CG8410 is optimised to deliver:

Good processability
High speed coating
Excellent moisture barrier properties

High grease resistance
Low friction
Increased surface hardness and stiffness

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	941 kg/m ³	ISO 1183
Melt Flow Rate (190 °C/2,16 kg)	7,5 g/10min	ISO 1133
Maximum Coating Speed	500 m/min	BTM 14921
Minimum Coating Weight	8 g/m ²	BTM 14922
Total Neck-in	95 mm	BTM 14920

Storage

CG8410 should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

Safety

The product is not classified as a dangerous preparation.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety of the product.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168



Polyethylene CG8410



扫一扫上面的二维码图案，加我为朋友。

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"
Statement on chemicals, regulations and standards
General statement on compliance to food contact regulations

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of Borealis' products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.