

Polyethylene **MG9641**



扫一扫上面的二维码图案，加我为朋友。

Description

MG9641 is a high density polyethylene This grade is designed for the injection moulding of articles which require good rigidity, good flow properties and high impact strength.

Applications

Crates
Snow pulcas

Special features

Good flow behaviour
Good impact strength

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	964 kg/m ³	ISO 1183
Melt Flow Rate (190 °C/2,16 kg)	8 g/10min	ISO 1133
Tensile Modulus (1 mm/min) ¹	1.250 MPa	ISO 527-2
Tensile Strain at Yield (50 mm/min) ¹	8 %	ISO 527-2
Tensile Stress at Yield (50 mm/min) ¹	29 MPa	ISO 527-2
Heat Deflection Temperature (0,45 MPa) ¹	75 °C	ISO 75-2
Charpy Impact Strength, notched (23 °C)	6 kJ/m ²	ISO 179/1eA
Charpy Impact Strength, notched (-20 °C)	5 kJ/m ²	ISO 179/1eA
Hardness, Shore D	63	ISO 868

¹ Measured on injection moulded specimens acc. to ISO 1872-2

Processing Techniques

Following parameters should be used as guidelines:

Injection Moulding

Melt temperature	210 - 275 °C	
Holding pressure	As low as possible	Minimum to avoid sink marks.
Mould temperature	10 - 40 °C	
Injection speed	As high as possible.	

Shrinkage 1 - 2 %, depending on wall thickness and moulding parameters

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168



Polyethylene MG9641



扫一扫上面的二维码图案，加我为朋友。

Storage

MG9641 should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

Safety

The product is not classified as dangerous.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"
Statement on compliance to food contact regulations

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of Borealis' products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168