



扫一扫上面的二维码图案，加我为朋友。

# Polyethylene FA6220

Low density polyethylene for Film Extrusion

## Description

**FA6220** is a Low Density Polyethylene for Film Extrusion. Autoclave Technology. Includes Antioxidant.

This grade is developed for the production of thin blown films.

**CAS-No.** 9002-88-4

## Applications

**FA6220** has been developed especially for applications like:

Shrink film  
Pouches

General packaging film  
Bubble film and foam

## Additives

**FA6220** contains antioxidant.

## Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	922 kg/m <sup>3</sup>	ISO 1183
Melt Flow Rate (190 °C/2,16 kg)	2,1 g/10min	ISO 1133
Melting temperature	111 °C	ISO 11357-3

## Film Properties

Film properties are measured on 40 µm film sample produced on a 60 mm W&H extruder with IBC cooling at BUR = 1:2,5.

Property	Typical Value	Test Method
Data should not be used for specification work		
Dart Drop	100 g	ISO 7765-1
Puncture resistance	1,3 J	ASTM D 5748
Haze	7 %	ASTM D 1003
Gloss	85	ASTM D 2457
Tensile Strain at Break <sup>1</sup>	MD 350 %	ISO 527-3
Tensile Strain at Break	TD 600 %	ISO 527-3
Tensile Strength	MD 26 MPa	ISO 527-3
Tensile Strength	TD 20 MPa	ISO 527-3
Tensile Modulus	MD 200 MPa	ASTM D 882-A
Tensile Modulus	TD 210 MPa	ASTM D 882-A
Tear resistance (Elmendorf)	MD 5 N	ISO 6383/2
	TD 3 N	
Coefficient of friction (Dynamic)	0,9	ISO 8295

<sup>1</sup> MD = machine direction, TD = transverse direction.

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168



扫一扫上面的二维码图案，加我为朋友。

# Polyethylene FA6220

## Processing Techniques

FA6220 is easily processed on conventional extruders.

With suitable equipment FA6220 can be drawn down to 25 micron.

Recommended melt temperature range is from 150°C to 180°C.

Due to differences in screw and die head designs the optimum temperature adjustments are individual and should be sought for each production line.

## Storage

**FA6220** should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet".

## Safety

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

## Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

## Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"  
Statement on chemicals, regulations and standards  
Statement on polymer additives and BSE  
Statement on compliance to food contact regulations