



扫一扫上面的二维码图案，加我为朋友。

Polyethylene FA5223

Low density polyethylene for Film Extrusion

Description

FA5223 is a Low Density Polyethylene for Film Extrusion. Autoclave Technology. Contains Antioxidant and Anti-block additive.

This grade is developed to give strong film for medium duty applications.

CAS-No. 9002-88-4

Applications

FA5223 has been developed especially for applications like:

Heavy-duty sack
Food packaging
Shrink film

Carrier-bag film
Pouches
General packaging film

Additives

	Content	
Antiblock (Talc)	850 ppm	Borealis Method
Antioxidant	Yes	Borealis Method

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	922 kg/m ³	ISO 1183
Melt Flow Rate (190 °C/2,16 kg)	1,2 g/10min	ISO 1133
Melting temperature	110 °C	ISO 11357-3

Film Properties

Film properties are measured on 40 µm film sample produced on a 60 mm W&H extruder with IBC cooling at BUR = 1:2,5.

Property	Typical Value	Test Method
Data should not be used for specification work		
Dart Drop	140 g	ISO 7765-1
Puncture resistance	2 J	ASTM D 5748
Haze	8 %	ASTM D 1003
Gloss	85	ASTM D 2457
Tensile Strain at Break ¹	MD 300 %	ISO 527-3
Tensile Strain at Break	TD 500 %	ISO 527-3
Tensile Strength	MD 26 MPa	ISO 527-3
Tensile Strength	TD 23 MPa	ISO 527-3
Tensile Modulus	MD 180 MPa	ASTM D 882-A
Tensile Modulus	TD 180 MPa	ASTM D 882-A
Tear resistance (Elmendorf)	MD 4 N	ISO 6383/2

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168



扫一扫上面的二维码图案，加我为朋友。

Polyethylene FA5223

Coefficient of friction (Dynamic)	TD 2 N 0,8	ISO 8295
-----------------------------------	---------------	----------

¹ MD = machine direction, TD = transverse direction.

Processing Techniques

FA5223 is easily processed on conventional extruders.

With suitable equipment FA5223 can be drawn down to 25-30 micron.

Recommended melt temperature range is from 160°C to 190 °C.

Due to differences in screw and die head designs the optimum temperature adjustments are individual and should be sought for each production line.

Storage

FA5223 should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet".

Safety

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"
Statement on chemicals, regulations and standards
Statement on polymer additives and BSE
Statement on compliance to food contact regulations

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168