



扫一扫上面的二维码图案,加我为朋友。

Linear Low Density Polyethylene for Film Extrusion

Description

Borstar FB2310 is a high molecular weight linear low density polyethylene film grade combining good and flexible extrusion behaviour, excellent draw down and superior mechanical properties

For films made of Borstar FB2310, the high toughness remains in cold conditions.

Applications

Borstar FB2310 has been developed especially for applications like:

Agricultural films Food packaging Frozen food packaging Heavy-duty sack Shrink film Protective film

Additives

Borstar FB2310 contains antioxidant.

Physical Properties

Property	Typical Value Test Method Data should not be used for specification work	
Density Melt Flow Rate (190 °C/2,16 kg) Melt Flow Rate (190 °C/5 kg) Melt Flow Rate (190 °C/21,6 kg) Melting temperature (DSC)	931 kg/m3 0,2 g/10min 0,9 g/10min 20 g/10min 127 °C	ISO 1183 ISO 1133 ISO 1133 ISO 1133 ISO 1133 ISO 11357-3

HongRong Engineering Plastics Co.,Ltd. Head Office Tel. +85–2–6957–5415 Research Center Tel.+188 1699 6168







扫一扫上面的二维码图案,加我为朋友。

Film Properties

Film properties are measured on 40 µm blown film produced on a 60 mm W&H extruder with L/D 30 and die 200 x 1,2 mm, BUR = 3:1, FLH = 2DD.

Property		Typical Value Data should not be used f	Test Method or specification work	
Dart Drop		230 g	ISO 7765-1	
Instrumented puncture test	Total Penetration Energy	20 J/mm	ISO 7765-2	
Haze		80 %	ASTM D 1003	
Gloss		7	ASTM D 2457	
Tensile Strain at Break ¹	MD	400 %	ISO 527-3	
Tensile Strain at Break	TD	700 %	ISO 527-3	
Tensile Strength	MD	50 MPa	ISO 527-3	
Tensile Strength	TD	40 MPa	ISO 527-3	
Tensile Modulus	MD	300 MPa	ISO 527-3	
Tensile Modulus	TD	400 MPa	ISO 527-3	
Tear resistance (Elmendorf)	MD	50 N/mm	ISO 6383/2	
	TD	250 N/mm		
Coefficient of friction (Dynamic)	1	0,4	ISO 8295	

¹ MD = machine direction, TD = transverse direction.

Processing Techniques

Borstar FB2310 is easily processed on conventional extruders.

Borstar FB2310 can be processed in most types of blown film equipment, incl. LDPE, LLDPE or even HDPE extruders. The balance of draw down properties and bubble stability is superior to conventional LLDPE and LDPE. Thicknesses of 10 to >200µm can be processed with good bubble stability. **Borstar FB2310** is well suited for co-extrusion.

Recommended extrusion temperature is 190°C-210°C. Conventional die gaps can be used without sharkskin or draw down problems. A gap of 1,0-1,5 mm will give the best balance between extruder pressure and physical properties in the film. Wider die gap gives higher machine direction orientation and narrow die gap may give too high extruder pressure.

Borstar FB2310 is sensitive to the orientation obtained by the film blowing conditions like Blow Up Ration (BUR) and Frost Line Height (FLH). Higher impact can be achieved by rising the FLH and 4DD. High BUR (>2) also results in better mechanical properties and better balance in MD/TD.

Storage

Borstar FB2310 should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet".

HongRong Engineering Plastics Co.,Ltd. Head Office Tel. +85-2-6957-5415 Research Center Tel.+188 1699 6168





扫一扫上面的二维码图案,加我为朋友。

Borstar FB2310

Safety

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the products. For more information, contact your Borealis representative.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet" Statement on chemicals, regulations and standards Statement on polymer additives and BSE General statement on compliance to food contact regulations

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of Borealis' products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

HongRong Engineering Plastics Co.,Ltd. Head Office Tel. +85–2–6957–5415 Research Center Tel.+188 1699 6168

