

Description

FT5236 is a low density polyethylene based on the tubular technology for film extrusion, containing anti-block and slip additives. This grade is developed for the production of packaging film with good optical properties for medium duty film applications.

CAS-No. 9002-88-4

Applications

FT5236 is intended for:

Carrier-bag film
Pouches
Lamination films
Food packaging

Additives

	Content		
Antiblock (Synthetic Silica)	800 ppm	Borealis Method	
Slip (Erucamide)	550 ppm	Borealis Method	
Antioxidant	Yes	Borealis Method	

Physical Properties

Property	Typical Value Test Method Data should not be used for specification work		
Density	923 kg/m³	ISO 1183	
Melt Flow Rate (190 °C/2,16 kg)	0,75 g/10min	ISO 1133	
Melting temperature	112 °C	ISO 11357-3	

Film Properties

Film properties are measured on 40 μ m film sample produced on a 60 mm W&H extruder with IBC cooling at BUR = 1:2,5.

Property		Typical Value Test Method Data should not be used for specification work		
Dart Drop		120 g	ISO 7765-1	
Instrumented puncture test T	Total Penetration Energy	2,5 J	ISO 6603-2	
Haze		8 %	ASTM D 1003	
Gloss at 20 degree (of arc)		85	ASTM D 2457	
Tensile Strain at Break 1	MD	250 %	ISO 527-3	
Tensile Strain at Break	TD	550 %	ISO 527-3	
Tensile Strength	MD	27 MPa	ISO 527-3	
Tensile Strength	TD	24 MPa	ISO 527-3	
Tensile Modulus	MD	230 MPa	ASTM D 882-A	
Tensile Modulus	TD	260 MPa	ASTM D 882-A	
Tear resistance (Elmendorf)	MD	4 N	ISO 6383-2	
	TD	2 N		
Coefficient of friction (Dynamic)		0,2	ISO 8295	

¹ MD = machine direction, TD = transverse direction.

HongRong Engineering Plastics Co.,Ltd. Head Office Tel. +85-2-6957-5415 Research Center Tel.+188 1699 6168





Processing Techniques

FT5236 is easily processed on conventional extruders. Recommended melt temperature range is from 160°C to 190°C.

With suitable equipment FT5236 can be drawn down to 30 micron.

Due to differences in screw and die head designs the optimum temperature adjustments are individual and should be sought for each production line.

Storage

FT5236 should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet".

Safety

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet" Statement on chemicals, regulations and standards Statement on Origin of Raw Materials General statement on compliance to food contact regulations



HongRong Engineering Plastics Co.,Ltd. Head Office Tel. +85-2-6957-5415 Research Center Tel.+188 1699 6168



Issuer:

Marketing Consumer Products / Mari Kylmala Product Management / Jenny Wang

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.



HongRong Engineering Plastics Co.,Ltd. Head Office Tel. +85-2-6957-5415 Research Center Tel.+188 1699 6168