



Polyethylene

# Borstar® FB4230

Linear Low Density Polyethylene for Film Extrusion

## Description

**Borstar FB4230** is a linear low density polyethylene film grade combining good and flexible extrusion behaviour, excellent draw down and superior mechanical properties.

Blown film extrusion with Borstar LLDPE is comparable to LDPE, but with better flexibility in film thickness range and draw down.

## Applications

**Borstar FB4230** has been developed especially for applications like:

Food packaging  
Pouches  
General packaging

Frozen food packaging

## Additives

**Borstar FB4230** contains antioxidant.

## Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	923 kg/m <sup>3</sup>	ISO 1183
Melt Flow Rate (190 °C/2,16 kg)	0,4 g/10min	ISO 1133
Melt Flow Rate (190 °C/5,0 kg)	2,0 g/10min	ISO 1133
Melt Flow Rate (190 °C/21,6 kg)	44 g/10min	ISO 1133
Melting temperature (DSC)	124 °C	ISO 11357-3

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168



# Polyethylene Borstar FB4230

## Film Properties

Film properties are measured on 40 µm blown film produced on a 60 mm W&H extruder with L/D 30 and die 200 x 1,2 mm, BUR = 3:1, FLH = 2DD.

Property	Typical Value	Test Method
Data should not be used for specification work		
Dart Drop	175 g	ISO 7765-1
Instrumented puncture test	15 J/mm	ISO 7765-2
Haze	70 %	ASTM D 1003
Gloss at 20 degree (of arc)	10	ASTM D 2457
Tensile Strain at Break <sup>1</sup>	MD 500 %	ISO 527-3
Tensile Strain at Break	TD 750 %	ISO 527-3
Tensile Strength	MD 50 MPa	ISO 527-3
Tensile Strength	TD 40 MPa	ISO 527-3
Tensile Modulus	MD 300 MPa	ISO 527-3
Tensile Modulus	TD 350 MPa	ISO 527-3
Tear resistance (Elmendorf)	MD 70 N/mm	ISO 6383/2
	TD 200 N/mm	
Coefficient of friction (Dynamic)	0,4	ISO 8295

<sup>1</sup> MD = machine direction, TD = transverse direction.

## Processing Techniques

Borstar FB4230 is easily processed on conventional extruders.

Borstar FB4230 can be processed in most types of blown film equipment, incl. HDPE and LLDPE or LDPE extruders. The balance of draw down properties and bubble stability is superior to conventional LLDPE and LDPE. Thickness of 10 to >200µm can be processed with good bubble stability. Borstar FB4230 is especially well suited for co-extrusion. Borstar FB4230 will in most cases provide an improvement of production regularity.

Recommended extrusion temperature is 180°C-210°C. Conventional die gaps can be used without shark skin or draw down problems. A gap of 1,0-1,5 will give the best balance between extruder pressure and physical properties in the film. Wider die gap gives higher machine direction orientation and narrow die gap may give too high extruder pressure.

## Storage

**Borstar FB4230** should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet".

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168



Polyethylene

# Borstar FB4230

## Safety

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

## Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

## Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"

Statement on chemicals, regulations and standards

Statement on polymer additives and BSE

Statement on compliance to food contact regulations