

Crosslinkable Insulation Compound

Description

Borlink LS4201R is a crosslinkable natural polyethylene compound based on Supercure technology, specially designed for insulation of energy cables.

Applications

Borlink LS4201R is intended for insulation of XLPE power cables with rated voltages up to 72 kV.

Specifications

Borlink LS4201R meets the applicable requirements as below when processed using sound extrusion practices and testing procedures

IEC 60502-2 ICEA S-108-720 IEC 60840 Cenelec HD 620 S1, Part 1, table 2A, DIX 3-14

Special features

Borlink LS4201R is a ready-to-use natural compound. Thanks to its inherent properties, Borlink LS4201R provides very good electrical performance. It offers excellent scorch resistance and long production runs. Borlink LS4201R cleanliness level is assured through the Borealis quality control system.

Physical Properties

Property	Typical Value Data should not be used for sp	Test Method ecification work
Density (Base Resin) Melt Flow Rate (190 °C/2,16 kg) ¹ Tensile Strain at Break (250 mm/min) ² Tensile Strength (250 mm/min) ² Change of Tensile Properties After Ageing (168 h, 135 °C)	922 kg/m³ 2 g/10min > 450 % > 17 MPa < 20 %	ISO 1872-2/ISO 1183 ISO 1133 ISO 527 ISO 527 IEC 60811-401
Hot Set Test (200 °C, 0,20 MPa)Elongation under load Permanent deformationGöttfert Elastograph Scorch Time (t10) Methanol Wash 3 MoistureNoisture	75 % 5 % 0,56 - 0,67 Nm 1,0 min 800 ppm < 200 ppm	IEC 60811-507 ISO 6502 ISO 6502 BTM 00118 Karl Fischer-titration

¹ Base Resin

² Measured on crosslinked specimens

³ BTM = Borealis Test Method

HongRong Engineering Plastics Co.,Ltd. Head Office Tel. +85–2–6957–5415 Research Center Tel.+188 1699 6168



Borlink LS4201R

Electrical Properties

Property	Typical Value Test Method Data should not be used for specification work	
Dielectric constant (50 Hz)	2,3	IEC 60250
DC Volume Resistivity	> 10 POhm.cm	IEC 60093
Dielectric Strength (50 Hz)	> 30 kV/mm	IEC 60243
Dissipation Factor (50 Hz)	0,0003	IEC 60250

Processing Techniques

To produce a good and reliable cable, it is essential to ensure careful and very clean handling of the insulation material. Hence all material handling should preferably be conducted in closed systems and in clean room conditions. Please contact your Borealis representative for more details.

Extrusion Melt temperature

125 - 135 °C

Packaging

Package:

Octabins Smallbins Cleantainers

Storage

Borlink LS4201R has a shelf life of 12 months from production date if stored in unopened original packages, under dry and clean conditions at temperatures between 10 - 30 °C (50 - 85 °F). The material could be stored (originally closed and in dry environment) at an ambient temperature up to 40 °C for a certain period of time (6 months) without negative influence on the material quality. Before use, material shall be conditioned indoors (production room) at the ambient temperature.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet" for this product.

Safety

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety of the product. For more information, contact your Borealis representative.

HongRong Engineering Plastics Co.,Ltd. Head Office Tel. +85–2–6957–5415 Research Center Tel.+188 1699 6168





Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.

HongRong Engineering Plastics Co.,Ltd. Head Office Tel. +85-2-6957-5415 Research Center Tel.+188 1699 6168

