

Crosslinkable Insulation Compound

Description

Borlink LE4201R is a crosslinkable natural polyethylene compound, specially designed for insulation of energy cables.

Applications

Borlink LE4201R is intended for insulation of XLPE power cables with rated voltages up to 72 kV.

Specifications

Borlink LE4201R meets the applicable requirements as below when processed using sound extrusion practices and testing procedures

IEC 60502-2

IEC 60840

Cenelec HD 620 S1, Part 1, table 2A, DIX 3-14 ICEA S-108-720

Physical Properties

Property		Typical Value Test Method Data should not be used for specification work		
Density (Base Resin)		922 kg/m³	ISO 1183	
Melt Flow Rate (190 °C/2,16 kg) ¹		2 g/10min	ISO 1133	
Tensile Strain at Break (250 mm/min) ²		> 450 %	ISO 527	
Tensile Strength (250 mm/min) ²		> 17 MPa	ISO 527	
Change of Tensile Properties After Ageing (168 h, 135 °C)		< 20 %	IEC 60811-401	
Hot Set Test (200 °C, 0,20	Elongation under load	75 %	IEC 60811-507	
MPa)	Permanent deformation	5 %		
Göttfert Elastograph		0,59 - 0,74 Nm	ISO 6502	
Scorch Time (10) Methanol Wash ³ Moisture		0,8 min	ISO 6502	
		< 1.000 ppm	BTM 00118	
		< 200 ppm	Karl Fischer-titration	
¹ Base Resin				

² Measured on crosslinked specimens

 3 BTM = Borealis Test Method

Electrical Properties

Property	Typical Value Data should not be used for speci	Test Method fication work
Dielectric constant (50 Hz)	2,3	IEC 60250
DC Volume Resistivity	10 POhm.cm	IEC 60093
Dielectric Strength (50 Hz)	> 22 kV/mm	IEC 60243
Dissipation Factor (50 Hz)	0,0003	IEC 60250

HongRong Engineering Plastics Co.,Ltd. Head Office Tel. +85–2–6957–5415 Research Center Tel.+188 1699 6168



Borlink LE4201R

Processing Techniques

To produce a good and reliable cable, it is essential to ensure careful and very clean handling of the insulation material. Hence all material handling should preferably be conducted in closed systems and in clean room conditions. Practical advice is given in a separate brochure. Please contact your Borealis representative for more details.

Extrusion

Melt temperature

125 - 135 °C

Packaging

Package:

Octabins Smallbins

Storage

Borlink LE4201R has a shelf life of 12 months from delivery date if stored in unopened original packages, under dry and clean conditions at temperatures between 10 - 30 °C (50 - 85 °F). The material could be stored (originally closed and in dry environment) at an ambient temperature up to 40°C for a certain period of time (6 months) without negative influence on the material quality. Before use, material shall be conditioned indoors (production room) at the ambient temperature.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet" for this product.

Safety

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety of the product. For more information, contact your Borealis representative.

HongRong Engineering Plastics Co.,Ltd. Head Office Tel. +85-2-6957-5415 Research Center Tel.+188 1699 6168





Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.

HongRong Engineering Plastics Co.,Ltd. Head Office Tel. +85–2–6957–5415 Research Center Tel.+188 1699 6168

