

Polyethylene Based Striping Compound for Primary Automotive Wires

Description

FR4847 is a Polyethylene Based Striping Compound for Primary Automotive Wires.

FR4847 is designed and manufactured with advanced material and processing technology to provde enhanced stabilization and lower particulate matter. This compound was designed to have high compatability with our chemically crosslinkable non-halogen flame retardant insulation compounds.

APPLICATION: **FR4847** is intended for use as non-halogen flame retardant polyethylene compound in striping applications for primary automotive wires. It would be used in conjunction with our chemically crosslinkable non-halogen flame retardant insulation compounds.

Physical Properties

Property	Typical Value Data should not be used for specifica	Test Method ation work
Density (Compound) (23 °C) Tensile Strain at Break Tensile Strength Hardness, Shore D	1400 kg/m3 280 % 9 MPa 48	ASTM D 792 ASTM D 412 ASTM D 2240

Electrical Properties

Property	Typical Value Data should not be used for specific	Test Method ation work
Dielectric constant (60 Hz) ¹ DC Volume Resistivity Dielectric Strength Dissipation Factor (60 Hz) ¹	3,7 10 POhm.cm > 22 kV/mm 0,01	ASTM D 150 ASTM D 257 ASTM D 150

¹ 23 °C

Processing Techniques

Please contact your Borealis representative for more details.

The following conditions may be used as a guide when starting up the extruder.Drying (2 - 8 h)55 °CBarrel121 °CMax allowed Melt temperature120 - 125 °C

HongRong Engineering Plastics Co.,Ltd. Head Office Tel. +85-2-6957-5415 Research Center Tel.+188 1699 6168





Packaging

Package:

Bulk Smallbins

Storage

FR4847 has a shelf life of 12 months from delivery date if stored in unopened original packages, under dry and clean conditions at temperatures between 10 - 30 °C (50 - 85 °F).

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of Borealis' products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

HongRong Engineering Plastics Co.,Ltd. Head Office Tel. +85-2-6957-5415 Research Center Tel.+188 1699 6168

